Amended Safety Assessment of Acrylates Copolymers as Used in Cosmetics

Status: Release Date: Panel Meeting Date: Tentative Amended Report for Public Comment October 5, 2018 December 3-4, 2018

All interested persons are provided 60 days from the above date to comment on this safety assessment and to identify additional published data that should be included or provide unpublished data which can be made public and included. Information may be submitted without identifying the source or the trade name of the cosmetic product containing the ingredient. All unpublished data submitted to CIR will be discussed in open meetings, will be available at the CIR office for review by any interested party and may be cited in a peer-reviewed scientific journal. Please submit data, comments, or requests to the CIR Executive Director, Dr. Bart Heldreth.

The 2018 Cosmetic Ingredient Review Expert Panel members are: Chair, Wilma F. Bergfeld, M.D., F.A.C.P.; Donald V. Belsito, M.D.; Ronald A. Hill, Ph.D.; Curtis D. Klaassen, Ph.D.; Daniel C. Liebler, Ph.D.; James G. Marks, Jr., M.D., Ronald C. Shank, Ph.D.; Thomas J. Slaga, Ph.D.; and Paul W. Snyder, D.V.M., Ph.D. The CIR Executive Director is Bart Heldreth, Ph.D. This safety assessment was prepared by Monice M. Fiume, Senior Director.

© Cosmetic Ingredient Review 1620 L Street, NW, Suite 1200 ◊ Washington, DC 20036-4702 ◊ ph 202.331.0651 ◊ fax 202.331.0088 ◊ <u>cirinfo@cir-safety.org</u>

ABSTRACT

The Cosmetic Ingredient Review (CIR) Expert Panel (Panel) assessed the safety of 126 acrylates copolymers; 56 of these ingredients were previously reviewed by the Panel, and 70 are reviewed herein for the first time. Many of these ingredients are reported to have several functions in cosmetics, with the function of film former being the most commonly reported cosmetic function for members of this family; many of the ingredients also may function in cosmetics as viscosity increasing agents. The Panel reviewed relevant new data, including frequency and concentration of use, and considered the data from previous CIR reports. The Panel concluded the 126 acrylates copolymers named in this report are safe in cosmetics in the present practices of use and concentration described in the safety assessment when formulated to be non-irritating.

INTRODUCTION

CIR published the Final Report on the Safety Assessment of Acrylates Copolymer and 33 Related Cosmetic Ingredients in 2002.¹ Based on the available data, the Panel concluded that the acrylates copolymers named in that report are safe for use in cosmetics when formulated to avoid irritation.

According to its Procedures, the CIR evaluates the conclusions of previously-issued reports every 15 years. As part of the rereview process, in addition to reassessing the existing conclusion, CIR also determines whether other ingredients are appropriate for inclusion in the re-review document. The Panel determined that it is appropriate to include all the copolymers (including crosslinked copolymers (i.e., crosspolymers)) prepared from monomers that comprise, in part, acrylic acid and/or methacrylic acid; the methyl, ethyl, propyl, or butyl ester(s) of these acids; or the salts of one or both of these two acids, with a few exceptions, as described below. Based on this rationale, the 126 ingredients described below, and listed in Table 1, are included in this re-review.

Some of the ingredients deemed appropriate for inclusion have previously been reviewed by CIR in other assessments. In 2017, the Panel published a safety assessment with the conclusion that 23 crosslinked alkyl acrylates included in the safety assessment are safe in the present practices of use and concentration, except when polymerized in benzene; Acrylates C10-30 Alkyl Acrylate Crosspolymer may be polymerized in benzene, and the available data were insufficient to make a determination of safety for this ingredient when polymerized in benzene.² Because the data were insufficient for Acrylates C10-30 Alkyl Acrylate Crosspolymer polymerized in benzene, this assessment will only review the safety of Acrylates C10-30 Alkyl Acrylate Crosspolymer in solvents other than benzene.

In 2011, the Panel published a safety assessment of Polymethyl Methacrylate (PMMA), Methyl Methacrylate Crosspolymer, and Methyl Methacrylate/Glycol Dimethacrylate Crosspolymer, and concluded that these ingredients are safe in the practices of use and concentration that were described in the report.³ The Food and Drug Administration (FDA) determination of safety of PMMA use in several medical devices, which included human and animal safety data. The Panel used that information as the basis of safety of PMMA and related polymers as used in cosmetics.

Another report on similar ingredients is the 1982 CIR Final Report on the Safety Assessment of Carbomers-934, -910, -934P, 940, -941, and -962; the Panel concluded that these ingredients are safe in the present practices of use and concentration that were described in that report.⁴ These ingredient names no longer exist as INCI names. Instead, they are now identified in the web-based *International Cosmetic Ingredient Dictionary and Handbook* (wINCI; *Dictionary*) as technical names for one ingredient, Carbomer.⁵ In 2003, the Panel reaffirmed that Carbomer is safe as used.⁶

In addition to the ingredients that have been previously reviewed by the Panel, an additional 70 acrylates copolymers that have not yet been reviewed are named in the *Dictionary*.⁵ These ingredients are also included in this safety assessment.

The Panel determined that it was appropriate to exclude five ingredients that were part of the initial safety assessment on the Acrylates Copolymers in this re-review because they are either already part of a recent or a concurrent safety assessment. Sodium Styrene/Acrylates Copolymer and Styrene/Acrylates Copolymer were reviewed in 2014 (and found safe as used in cosmetics),⁷ and the safety of Acrylates/VP Copolymer, Vinyl Caprolactam/VP/Dimethylaminoethyl Methacrylate Copolymer, and VP/Dimethyl-aminoethylmethacrylate Copolymer are part of the concurrent safety assessment of Vinylpyrrolidone Polymers.

According to the *Dictionary*, the ingredients included in this report have an array of functions in cosmetics, with the function of film former being the most commonly reported cosmetic function for members of this family (Table 2).⁵ Many of the ingredients also may function in cosmetics as viscosity increasing agents.

This safety assessment includes relevant published and unpublished data that are available for each endpoint that is evaluated. Published data are identified by conducting an exhaustive search of the world's literature. A listing of the search engines and websites that are used and the sources that are typically explored, as well as the endpoints that CIR typically evaluates, is provided on the CIR website (<u>http://www.cir-safety.org/supplementaldoc/preliminary-search-engines-and-websites; http://www.cir-safety.org/supplementaldoc/cir-report-format-outline</u>). Unpublished data are provided by the cosmetics industry, as well as by other interested parties.

Excerpts from the summaries of previous reports on Acrylates Copolymer and related ingredients, and all other previouslyreviewed ingredients, are disseminated throughout the text of this re-review document, as appropriate, and are identified by *italicized text*. (This information is not included in the tables or the summary section.) Additionally, the Discussions from these reports are also included in this document. For complete and detailed information, please refer to the original documents, which are available on the CIR website (<u>http://www.cir-safety.org/ingredients</u>). Please note that information on the monomers is found in several of the original reports, but not in this document. Much of the new data included in this safety assessment was published by Australia's National Industrial Chemicals Notification and Assessment Scheme (NICNAS).⁸⁻¹⁴ Please note that NICNAS provides summaries of information generated by industry, and it is that summary data that are brought into this safety assessment when NICNAS is cited.

CHEMISTRY

Definition and Structure

The definitions and structures of of the ingredients included in this report are provided in Table 2.

Copolymers are polymers synthesized from two or more different monomers, and crosspolymers are copolymers that are crosslinked (i.e., individual polymer chains are connected by bridging molecules [crosslinking agents]).² As stated in the Introduction, this report comprises a large number of copolymers and crosspolymers, most of which are prepared from monomers that include, in part, acrylic acid and/or methacrylic acid; the methyl, ethyl, propyl, or butyl ester(s) of these acids; or the salts of one or both of these two acids (Figure 1).



Figure 1. Acrylates copolymers, wherein R is hydrogen or methyl; R' is hydrogen, methyl, ethyl, propyl, butyl, or a salt cation (e.g., sodium); and X is one or more co-monomer residues.

However, a few of these ingredients are the polymerization products of monomers that comprise acrylate esters that are not methyl, ethyl, propyl, or butyl; but instead, these esters are the products of different alkoxyl or polyalkoxyl groups (Figure 1). Also, these other ingredients are all essentially homopolymers.



Figure 2. Other polyacrylates, wherein R is hydrogen or methyl; and R' is alkoxyl or polyalkoxyl (e.g., PEG-23).

Physical and Chemical Properties

From the Safety Assessment of Crosslinked Alkyl Acrylates²

Crosslinked polymers are generally less chemically reactive and less soluble (if not totally insoluble) than their respective non-crosslinked counterparts. Because of the manner in which these polymers are created and the mixture of monomers and cross-linking agents that can be used, 2 polymers that have the same INCI name can have very different physical consistencies.

Physical and chemical properties of several acrylates copolymers are described in Table 3. Primarily, physical form is identified therein.

Methods of Manufacture

From the Original Safety Assessment of Acrylates Copolymers¹

Linear polymers of acrylic acid are produced by combining the monomer with a free-radical initiator, which is generally largely consumed by the reaction. The size of the polymer is determined by controlling the environment in which the polymerization occurs. Polymers of acrylic acid are characterized by their average molecular weight, but many species of greater and lesser molecular weight are present and unreacted monomer and catalysts can also be present. Additionally, hydroquinone and monomethyl ester of hydroquinone are often incorporated into acrylic acid and its esters as an inhibitor.¹

Specific method of manufacture information for several ingredients is found in the original report.

From the Safety Assessment of Crosslinked Alkyl Acrylates²

Cross-linked alkyl acrylates are typically produced via free radical, head-to tail chain propagation polymerization. Ethyl acetate + cyclohexane, water, n-hexane, and benzene are all named as solvents.

From the Safety Assessment of PMMA and related ingredients³

The manufacturing process for PMMA beads used in medical devices and in cosmetic products is the same. The only difference is the size of the PMMA spheres, which are provided according to the specifications of the purchaser. Polymethyl methacrylate beads or powders in cosmetics are precipitated out from a polymerization reaction. The average bead size can be controlled within the 4 to 50 μ m specifications. In nail products, polymer powders are made from methyl or ethyl methacrylate or their copolymers.

From the Safety Assessment of [Carbomer]⁴

Carbomer is manufactured by reflux polymerization of acrylic acid in an inert solvent in the presence of a catalyst. In doing this, a closed system, free of oxygen and water, is used.

Acrylates Copolymer

Acrylates Copolymer, as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate, with a quantitative composition described as poly(ethyl acrylate-co-methyl methacrylate) 2:1, is produced by emulsion polymerization.¹⁵ A redox-initiated polymerization of the monomers ethyl acrylate and methyl methacrylate occurs through the use of a free radical donor redox initiator system. Polyethylene glycol monostearyl ether is used as an emulsifier in the process, and an alkyl mercaptan is used as a chain modifying agent. At the end of the process, an emulsifier is added to reduce foaming. Residual monomers and excess water are removed by water vapor distillation, and the pH of the reaction mixture is adjusted with sodium hydroxide.

A similar emulsion polymerization process is used to synthesize Acrylates Copolymer as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid, with a quantitative composition described as poly(methyl acrylate-comethyl methacrylate-co-methacrylic acid) 7:3:1 in an aqueous (aq.) medium.¹⁶ Polymerization is by means of a free radical initiator. Sodium lauryl sulfate (SLS) and polysorbate 80 are used as emulsifiers, and an alkyl mercaptan is used as a chain-modifying agent. Small amounts of dimethicone (polydimethyl siloxane) are added to reduce foam formation. Water vapor distillation removes the residual monomers to a level of less than 100 mg/kg total. After the reaction is cooled and filtered, the dry substance content is approximately 30%.

Composition/Impurities

From the Original Safety Assessment of Acrylates Copolymers¹

Linear polymers of acrylic acid may contain unreacted starting material and catalysts. Ten companies representing the majority of the production of polymers sold for cosmetic use indicated that residual acrylic acid concentrations in polymers are typically between 10 and 1000 ppm, with an upper limit of 1500 ppm.

One source reported Acrylates Copolymer can contain residual amounts of ≤ 20 ppm ethyl acrylate, methyl methacrylate, methacrylic acid, and acrylic acid; another source reported that three samples analyzed using gas chromatography (GC) contained < 0.2 to 0.8 ppm acrylic acid, 0.8 to 2.6 ppm methyl methacrylate, and 1.3 to 3.9 ppm ethylene glycol dimethacrylate. Additionally, it was reported to CIR that two polymers, both defined as Acrylates Copolymer, contained different residual monomers; the first contained 36, 20, and 45 ppm n-butyl acrylate, methyl methacrylate, and methacrylic acid, respectively, and the second contained 1500 and 200 ppm stearyl acrylate and methacrylic acid, respectively. Acrylates/VA Copolymer can contain, as reported by two polymer producers, 100 to 1000 ppm residual 2-ethylhexyl acrylate. However, the 10 respondents of the survey described previously reported that they did not produce acrylate polymers with 2-ethylhexyl acrylate for use in the cosmetic industry. Using UV spectroscopy with a limit of detection of 300 mg/kg (ppm), acrylic acid was detected in Polyacrylic Acid at 195 nm. A 90,000-Da molecular weight sodium hydroxide-neutralized Polyacrylic Acid contained 77.5% Sodium Polyacrylate, 3.3% free acrylic acid, and 18.1% water, whereas a 4500-Da molecular weight compound contained 43.3% solids and 0.09% residual monomer.

From the Safety Assessment of Crosslinked Alkyl Acrylates²

Small amounts of residual monomer and/or solvent may be present in the crosspolymers.

From the Safety Assessment of PMMA and related ingredients³

The impurity of concern in PMMA is the monomer, methyl methacrylate (MMA). Analysis of PMMA beads used in cosmetic formulations found MMA to be present at < 100 ppm. The Nail Manufacturers Council reported that the residual monomer is typically < 1.5%; averages of 0.7% and 1.2% have been reported. Residual MMA in Methyl Methacrylate Crosspolymer is similar to that found in PMMA, i.e., < 100 ppm.

From the Safety Assessment of [Carbomer]^{4,6}

Reported impurities for the Carbomer resins include water, benzene, propionic acid, acetic acid, acrylic acid, heavy metals, iron, arsenic, and lead. The Panel calls attention to the presence of benzene as an impurity in Carbomer and recommends that every effort be made to reduce it to the lowest possible value. However, when the safety of Carbomer was reassessed in 2003, the Panel acknowledged the industry practice of removing benzene from Carbomer.

Acrylates Copolymer

Specifications for Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) state that it contains < 100 mg/kg total monomer (sum of methyl methacrylate and ethyl acrylate); 0.7% residual emulsifier (polyethylene glycol monostearyl ether); < 0.5% ethanol; and < 0.1% methanol.¹⁷ Additionally, limits on heavy metals are: < 2 mg/kg arsenic; < 2 mg/kg lead; < 2 mg/kg mercury; < 10 mg/kg zinc; and < 10 mg/kg copper.

Approximately 0.3% SLS and 1.2% polysorbate 80, both w/w based on the solid substance, are residual in the polymer as a result of the emulsion polymerization process used to synthesize Acrylates Copolymer as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid.¹⁶

Acrylates/Steareth-20 Methacrylate Copolymer

Acrylates/Steareth-20 Methacrylate Copolymer contains < 100 ppm residual monomer.¹⁸

Polyacrylate-1 Crosspolymer

Polyacrylate-1 Crosspolymer is reported to be 99% pure.¹² (No other details were available.)

VA/Butyl Maleate/Isobornyl Acrylate Copolymer

A copolymer of vinyl acetate, butyl maleate and isobornyl acrylate in ethanol is reported to be at least 95.3% pure.⁸ Impurities are reported as < 0.4% acetone dimethylformaldehyde; < 0.1% vinyl acetate; < 0.1% monobutyl maleate; and < 0.1% isobornyl acrylate. The maximum percentage of low molecular weight species (molecular weight < 1000) is < 2%.

USE

Cosmetic

The safety of the cosmetic ingredients addressed in this report is evaluated based on data received from the US FDA and the cosmetics industry on the expected use of these ingredients in cosmetics. Use frequencies of individual ingredients in cosmetics are collected from manufacturers and reported by cosmetic product category in FDA's Voluntary Cosmetic Registration Program (VCRP) database. Use concentration data are submitted by the cosmetic industry in response to a survey, conducted by the Personal Care Products Council (Council), of maximum reported use concentrations by product category.

According to information received in 2018 from the VCRP and the Council survey, 66 of the 126 ingredients assessed in this report are in use.¹⁹⁻²⁴ Carbomer has the highest frequency of use; according to 2018 VCRP data, it is used in 6434 cosmetic formulations (with 6175 uses under the name Carbomer and 259 uses listed under various tradenames), and most of these uses (5336) are in leave-on products (Table 4).²⁴ Acrylates Copolymer and Acrylate/C10-30 Alkyl Acrylate Crosspolymer (solvent not specified) have the next highest frequencies of use, with 3177 and 3135 reported uses, respectively. Many of the other in-use acrylates copolymers have hundreds of use, although some have just a few.

The results of concentration of use surveys conducted by the Council in 2018 indicate that Acrylates Copolymer has the highest maximum use concentration; it is used at up to 98.6% in nail extenders; use in product categories other than nail products is not as high, but Acrylates Copolymer is used at up to 25% in products that result in dermal contact (face and neck products).¹⁹ Ingredients with the next highest reported concentrations of use are Acrylates/VA Copolymer (at 50%, in "other" skin care formulations)¹⁹ and Polymethyl Methacrylate (at up to 44.6%, in face powders).²³

Numerous ingredients named in this report have been reviewed previously by the Panel. For many of the previouslyreviewed ingredients, the frequency of use has increased since the time of the original review, with some increases being quite significant. For example, the frequency of use of Acrylates Copolymer increased from 227 uses in 1998¹ to 3177 uses in 2018,²⁴ and the frequency of use of Carbomer increased from 1504 uses in 2001⁶ to 3177 uses in 2018.²⁴ Concentrations of use were not reported by the FDA at the time of the original assessment of Acrylates Copolymer and related ingredients, so it is not known if the concentrations of use have changed for those ingredients. For the other previously-reviewed ingredients, there were no notable increases in concentrations of use.

In some cases, reports of uses were received from the FDA VCRP, but no concentration of use data were provided. For example, Potassium Carbomer is reported to be used in 73 formulations, but no use concentration data were submitted in response to the Council survey. In several other cases, no uses were reported to the VCRP, but a maximum use concentration was provided by industry. It should be presumed that for those ingredients, there is at least one use in each category for which a concentration was reported.

Many of the acrylates copolymers are used in products that can be used near the eye (e.g., 30% Acrylates/Ethylhexyl Acrylate Copolymer in mascara),²⁰ or are used in products that could result in incidental ingestion (e.g., 16.1% Polymethyl Methacrylate in lipstick formulations).²³ Additionally, some of these ingredients are used in cosmetic sprays and could possibly be inhaled; for example, VA/Butyl Maleate/Isobornyl Acrylate Copolymer is reported to be used at a maximum concentration of 10% in aerosol hair sprays). In practice, 95% to 99% of the droplets/particles released from cosmetic sprays have aerodynamic equivalent diameters > 10 μ m, with propellant sprays yielding a greater fraction of droplets/particles < 10 μ m compared with pump sprays.^{25,26} Therefore, most droplets/particles incidentally inhaled from cosmetic sprays would be deposited in the nasopharyngeal and thoracic regions of the respiratory tract and would not be respirable (i.e., they would not enter the lungs) to any appreciable amount.^{27,28}

Sodium Polyacrylate has reported use in an aerosol deodorant at a concentration of 2.9%.¹⁹ There is some evidence indicating that deodorant spray products can release substantially larger fractions of particulates having aerodynamic equivalent diameters in the range considered to be respirable.²⁸ However, the information is not sufficient to determine whether significantly greater lung exposures result from the use of deodorant sprays, compared to other cosmetic sprays. Additionally, some of the acrylates copolymers are reportedly used in loose powders; for example, Polymethyl Methacrylate is used at concentrations up to 44.6% in face powders,²³ and could possibly be inhaled. Conservative estimates of inhalation exposures to respirable particles during the use of loose powder cosmetic products are 400-fold to 1000-fold less than protective regulatory and guidance limits for inert airborne respirable particles in the workplace.²⁹⁻³¹

The 60 acrylates copolymers that are not reported to be in use according to 2018 FDA VCRP and 2018 Council survey data are listed in Table 5.

With the exception of AMP-Acrylates Copolymer, the acrylates copolymers described in this safety assessment are not restricted from use in any way under the rules governing cosmetic products in the European Union (EU).³² AMP-Acrylates Copolymer is restricted by a maximum secondary amine content of 5% in ready for use preparations.

Non-Cosmetic

From the Safety Assessment of PMMA and related ingredients³

Polymethyl methacrylate bone cement has been approved by the FDA as a class II (special controls) medical device that requires premarket notification and adherence to standards. Polymethyl methacrylate beads are incorporated into collagen as dermal fillers. Intraocular lenses are made of PMMA.

Several of the acrylates copolymers are approved for use as indirect food additives, per the Code of Federal Regulations.

Acrylates Copolymer

Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate¹⁵ and as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid¹⁶) is used as an excipient in the preparations for oral tablets as a glazing/coating agent to permit the pH-independent delayed release of active ingredients.

TOXICOKINETIC STUDIES

Dermal Penetration

From the Safety Assessment of PMMA and related ingredients³

Polymethyl methacrylate-based cosmetic ingredients are large molecules and remain in particulate form (dispersed) in final preparations and thus will not likely cross the stratum corneum to induce systemic toxicity.

Absorption, Distribution, Metabolism, and Excretion (ADME)

Animal

Oral

Acrylates Copolymer

Five male rats were administered 55 - 75 mg/animal of Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate; supplied as a dried film labeled with ¹⁴C with a specific activity of 0.17 μ Ci/mg) by gavage.¹⁵ Urine and feces were collected for 5 days prior to dosing (to establish background radioactivity levels), and for 7 days following dosing. Animals were then killed, and tissue samples were collected and assessed for radioactivity. An additional 9 male rats were also given a single oral dose of the test article, and 3 animals were killed 1, 3, or 14 days after dosing, and tissue samples were collected. The mean total recovery of radioactivity over a period of 5 days following administration of the labeled substance was in excess of 90% of the administered dose. More than 97% of the radioactivity was recovered in the feces, primarily with 48 h of dosing. Little radioactivity (0.0092%) was excreted in the urine. Levels of radioactivity in the blood and tissues did not significantly differ between treated and control animals. The researchers concluded that less than 0.02% of the administered test article was absorbed from the gastrointestinal tract, and that any material that was absorbed was rapidly excreted.

Three groups of 4 male and 4 female Sprague-Dawley rats were dosed by gavage for 13 days with Acrylates Copolymer (as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid; dose not stated), followed by a single dose of radiolabeled test material (10 mCi per animal; ¹⁴C-labeled at the free carboxyl group of the methacrylic acid moiety).¹⁶ One group was killed at 24 h, and one at 72 h, after the last dose. The last group was kept for 10 days, and urine and feces were collected. The majority of the dose was excreted in the feces; with 94% collected within 72 h of dosing. Little or no radioactivity (< 0.1%) was recovered in urine. Tissues and tissue contents accounted for < 0.01% of the total recovery, and levels of radioactivity in the carcass were below limits of detection.

TOXICOLOGICAL STUDIES

From the Safety Assessment of PMMA and related ingredients³

The Panel saw no need to review systemic toxicity data on PMMA and related polymers applied to the skin as the safety of this route of exposure can be extrapolated from data on use of these polymers as medical devices, which had already been reviewed and found safe by the FDA.

Acute Toxicity Studies

From the Original Safety Assessment of Acrylates Copolymers¹

The following LD_{50} values were reported for Acrylates Copolymer: > 16 g/kg (dermal, rabbits), > 16 ml/kg (dermal), >9 g/kg (dermal), 9 g/kg (dermal, rats), > 5.2 mg/l (rats). Ethylene/Acrylic Acid Copolymer had a" low order of acute toxicity" following dermal and oral administration to rats; the oral LD_{50} was > 5 g/kg. The oral LD_{50} for rats of an ammonium salt of Ethylene/Acrylic Acid was 41.5 ml/kg. In an acute inhalation study, 0 of 6 rats exposed to an aqueous emulsion of the ammonium salt of Ethylene/Acrylic Acid polymer died. The dermal LD_{50} for rabbits and the oral LD_{50} for rats of Vinyl Acetate/Maleate/Acrylate Copolymer solution was > 5 g/kg. For rats, the oral LD_{50} values of Polyacrylic Acid and Sodium Polyacrylate were 2.5 and > 40 g/kg, respectively; and 0.34 and 2.59 ml/kg, respectively, for male rats.

From the Safety Assessment of Crosslinked Alkyl Acrylates²

Little toxicity data were available; the acute dermal and oral toxicity data that were found indicated that these ingredients are not very toxic.

From the Safety Assessment of [Carbomer]⁴

Acute oral studies with rats, guinea pigs, mice, and dogs showed that Carbomer has low toxicity when ingested. The inhalation LC_{50} of Carbomer in albino rats was 1.71 mg/l. The dermal LD_{50} of rats exposed to Carbomer was > 3 g/kg.

The acute toxicity studies summarized here are described in Table 6. Dermal LD_{50} s of > 2 g/kg¹³ and > 5 g/kg¹⁴ were reported for Acrylates Copolymer in rats, and in rabbits, an LD_{50} of > 2 g/kg was reported for VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol.⁸ The dermal LD_{50} s of Acrylates/Beheneth-25 Methacrylate Copolymer¹⁰ and Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%) in rats¹⁴ were > 5 g/kg. Acute oral studies were conducted on Acrylates Copolymer; the LD_{50} s in rats and dogs were > 25.2 g dry copolymer/kg bw and > 7.95 g dry copolymer/kg bw, respectively.¹⁵ In oral studies in rats, LD_{50} s of > 5 g/kg were reported for Acrylates/Beheneth-25 Methacrylate Copolymer,¹⁰ Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%),¹⁴ and VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol.⁸ For Polyacrylate-1 Crosspolymer, the oral LD_{50} in rats was > 2 g/kg.¹² In acute inhalation studies in rats, a 4-h exposure resulted in LC_{50} s of > 3960 mg/l Acrylates Copolymer.¹⁵

Short-Term Toxicity Studies

From the Original Safety Assessment of Acrylates Copolymers¹

Pulmonary lesions were observed in rats used in short-term inhalation studies of acrylic acid polymers.

From the Safety Assessment of [Carbomer]⁴

Feeding of rats with doses up to 5.0 g/kg/day Carbomer (49 days) and of rats and dogs with up to 5.0% Carbomer in the diet (21 days) resulted in lower than normal body weights.

Oral

Acrylates Copolymer

Groups of 10 male and 10 female rats were dosed by gavage with 500, 1000, and 2000 mg/kg bw/day of dry Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) for 35 days.¹⁵ Two recovery groups of 5 males and 5 females were dosed with 0 or 2000 mg dry copolymer/kg bw/d and were used for a recovery period of 14 days without dosing. The control group received distilled water. No animals died during the study. Differences in hematology and clinical chemistry parameters and in organ weights that were observed between treated and control animals were not considered related to the test article because a dose-response was not observed. There were no changes in urinary parameters reported. The no-observed-adverse effect level (NOAEL) was 2000 mg/kg bw/day.

In a 28-day study, groups of 3 male and 3 female Göttingen minipigs were administered Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) via coating on cellulose pellets containing 22.7% copolymer.¹⁵ The animals received the coated cellulose pellets at dose levels of 500, 1000, and 2000 mg/kg bw/d, which corresponded to dose levels of 113, 227, and 454 mg/kg bw/d expressed as dry copolymer. Clinical signs were observed and feed consumption was measured daily, body weights were measured weekly, and hematology, clinical chemistry, urinalysis, and fecal parameters were evaluated. No treatment-related deaths were observed. There were no toxicologically relevant changes in body weight, food consumption, clinical observations, ophthalmoscopy, clinical pathology, urinalysis, fecal analysis, or in organ weights. Microscopic examination revealed instances of mucosal/submucosal edema in the cecum and colon of one male receiving 454 mg dry copolymer/kg bw/d and in the caecum of one male dosed at 227 mg dry copolymer/kg bw/d; the researcher commented that the

influence of the high doses is unclear, and the finding may be a physiological reaction of the intestine to the high amounts of nonsoluble or non-degradable particles resulting in osmotic imbalance. No toxicological relevance was attributed to this change. Centrilobular yellow/brown pigmentation and mild fibrosis was apparent in the liver of a single female dosed at 454 mg dry copolymer/kg bw/d. The NOAEL was determined to be 227 mg dry copolymer/kg bw/d.

Subchronic Toxicity Studies

From the Original Safety Assessment of Acrylates Copolymers¹

In a subchronic inhalation toxicity study of Acrylates Copolymer, alveolar histiocytosis was observed at a dose of 30 mg/m^3 . Pulmonary lesions were observed in rats used in subchronic inhalation studies of acrylic acid polymers.

From the Safety Assessment of [Carbomer]⁴

Subchronic feeding of rats and dogs with up to 5.0% Carbomer in the diet (90 days) resulted in lower than normal body weights. In rats fed Carbomer at dietary levels of 5.0% for 90 days, absolute liver weights and liver to body and brain weight ratios were reduced, but no pathological changes were observed.

Chronic Toxicity Studies

From the Original Safety Assessment of Acrylates Copolymers¹

In a chronic inhalation study of respirable polyacrylate particles, compound-related pulmonary lesions were not observed.

From the Safety Assessment of [Carbomer]⁴

When dogs were fed up to 1.0 g/kg/day for 6.5 or 32 months, and when rats chronically received less than 5.0% Carbomer in their diet (6.5 months), there was no significant effects. Rats fed Carbomer at dietary levels of 0.1%, 0.5%, or 5.0% for 6.5 months exhibited various organ weight changes. Dogs fed 0.5 or 1.0 g/kg/day Carbomer for 6.5 months manifested gastrointestinal irritation and marked pigment deposition within Kupffer cells of the liver.

Oral

Acrylates Copolymer

A 40% Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) dispersion was sprayed onto powdered diet at a ratio of 1:10, and the coated diet was mixed with basal diet and administered to groups of 20 male and 20 female Sprague-Dawley rats for 26 wks.¹⁵ Once mixed with basal diet, the dose levels were 500 and 2000 mg dry copolymer/kg bw/day. A control group of 20 males and 20 females received diet prepared by spraying with water and subsequent drying. The test was performed in accord with the Organisation for Economic Co-operation and Development (OECD) test guideline (TG) 408. Clinical signs were evaluated and feed consumption was measured daily, body weights were determined weekly, and clinical chemistry, hematology, and urinalysis parameters were evaluated at several intervals. All animals were killed at study termination. None of the animals died during the study, and no clinical signs of toxicity were observed. No treatment-related findings were observed. The NOAEL was \geq 2000 mg dry copolymer/kg bw/day.

A similar study was conducted using coated pellets containing approximately 22.7% Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate), and the pellets were placed into gelatin capsules and administered to groups of 4 male and 4 female Beagle dogs for 26 wks.¹⁵ The dose levels used were 50, 125, and 250 mg dry copolymer/kg bw/d, which were equivalent to 200, 500, and 1000 mg test material/kg bw/d. A control group of 4 males and 4 females were given empty capsules. An additional 3 male and 3 female animals were included with both the control and high dose groups, and these animals were allowed to recover for 3 wks after the termination of dosing. Examinations were made as described above. High-dose animals had lower body weight gains as compared to controls, and the difference became statistically significant at wk 12. Males of the low-and mid-dose groups had slightly lower body weights in treated females were increased, but these changes were not considered treatment-related because no differences were observed microscopically. Other observations were not considered toxicologically significant, and the NOAEL was determined to be 250 mg dry copolymer/kg bw/d.

DEVELOPMENTAL AND REPRODUCTIVE TOXICITY STUDIES

From the Original Safety Assessment of Acrylates Copolymers¹

Reproductive effects were not observed in a study in which rats were dosed orally with 4500- or 90,000-Da molecular weight Sodium Polyacrylate.

Oral

Acrylates Copolymer

Two studies were conducted in which an Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) dispersion was sprayed onto powdered diet at a ratio of 1:10, and the coated diet was mixed with basal diet for testing.¹⁵ In the first study, groups of 20 mated female Wistar rats were fed 0, 500, or 2000 mg dry copolymer/ kg bw/day on days 6 through 15 of gestation, and the gravid rats were killed on day 19 of gestation. In the second study, groups of 10 mated female New

Zealand White rabbits were given the same dosages on days 6 to 18 of gestation, and killed on day 29 of gestation. There were no signs of maternal toxicity in rats or rabbits, and there were no reproductive or developmental effects observed for either species. The NOAELs for dams and fetuses were 2000 mg/kg bw/day in both rats and rabbits.

GENOTOXICITY STUDIES

From the Original Safety Assessment of Acrylates Copolymers¹

Acrylates Copolymer was not mutagenic in Ames tests. A mixture containing 30% Ammonium Acrylates Copolymer was not mutagenic in a modified Ames test. Sodium Polyacrylate was not mutagenic in an Ames assay, a plate test, a mouse lymphoma assay, chromosomal aberration assays, an unscheduled DNA syntheses (UDS) assay, or an in vivo mouse micronucleus assay.

From the Safety Assessment of Crosslinked Alkyl Acrylates²

The little genotoxicity data that were available for the crosslinked alkyl acrylates reported negative results in Ames tests.

The genotoxicity studies summarized here are described in Table 7. Acrylates Copolymer (comprised of various monomer combinations) was not genotoxic in Ames tests (up to 5000 μ g dry copolymer/plate), mouse lymphoma L5178Y cell mutation assays (up to 6250 μ g dry copolymer/ml), or a chromosomal aberration assay (up to 9000 μ g dry copolymer/ml in human lymphocytes), and it was not genotoxic in the mouse micronucleus test in which mice were dosed with up to 2000 mg dry copolymer/kg bw.^{13,15,16} Acrylates/Hydroxyesters Acrylates Copolymer (in a product containing < 50%) was also not mutagenic in the Ames test.¹⁴ Details were missing from many of these studies.

CARCINOGENICITY STUDIES

Published carcinogenicity studies on the acrylates copolymers were not discovered in the published literature, and unpublished data were not submitted.

DERMAL IRRITATION AND SENSITIZATION STUDIES

From the Original Safety Assessment of Acrylates Copolymers¹

In dermal irritation studies using rabbits, Acrylates Copolymer was non- to mildly irritating. In one study, it produced signs of an irritant property. However, in a study in which the patches adhered to the skin, very slight to well-defined erythema, and severe erythema in one animal, were observed at 72 hours. A mixture containing 30% Ammonium Acrylates Copolymer was practically nonirritant, and an aqueous emulsion of the ammonium salt of an Ethylene/Acrylic Acid polymer produced minor irritation. Acrylates/VA Copolymer produced moderate to severe but reversible dermal irritation, Vinyl Acetate/ Maleate/Acrylate Copolymer solution had a primary irritation index of 4.4. Sodium Polyacrylate did not produce irritation. Acrylates Copolymer was not a sensitizer to guinea pigs in maximization studies or a Buehler sensitization test.

A 25% aq. dilution of Acrylates Copolymer was not an irritant or a sensitizer in a human repeated insult patch test (HRIPT; 47 subjects). In clinical testing, Acrylates Copolymer, 30% solids, was not an irritant or sensitizer, and neither was Acrylates Copolymer (100% solids) tested as a 15% solution in ammonia water or a 25% solution in acetone. Undiluted Sodium Polyacrylate did not produce irritation or sensitization in 50 subjects.

From the Safety Assessment of Crosslinked Alkyl Acrylates²

In an alternative method study, Acrylates/Vinyl Neodecanoate Crosspolymer was predicted to be a nonirritant. Studies in rabbits, guinea pigs, and humans reported no to slight irritation with undiluted and weak sensitization with 2% aq, Acrylates/C10-30 Alkyl Acrylate Crosspolymer, no irritation with Acrylates Crosspolymer at 30% in olive oil, and no irritation or sensitization with Sodium Acrylates Crosspolymer 2 (concentration not specified). Mostly, human testing with undiluted Acrylates/C10-30 Alkyl Acrylate Crosspolymer, Acrylates Crosspolymer, and Acrylates/Ethylhexyl Acrylate Crosspolymer, up to 2.5% aq. Acrylates/Vinyl Isodecanoate Crosspolymer, 1% aq. dilutions of formulations containing 2% Acrylates/Vinyl Neodecanoate Crosspolymer, and formulations containing up to 2.6% Lauryl Methacrylate/Glycol Dimethacrylate Crosspolymers do not indicate any dermal irritation or sensitization. The only exception was a weak irritant response noted during an intensified Shelanski HRIPT with undiluted Acrylate Crosspolymer.

While the residual monomer (MMA) has the potential to induce sensitization, the levels in these ingredients were reported to be well below the levels that would induce sensitization to MMA, thus resolving the Panel's concern about sensitization.

From the Safety Assessment of PMMA and related ingredients³

PMMA was not a dermal irritant to rabbits. *PMMA* was not irritating or sensitizing at 6.8% in an HRIPT test using 52 participants. The same result was obtained in another HRIPT test of PMMA at 2.0% (n = 106).

From the Safety Assessment of [Carbomer]⁴

Rabbits showed minimal skin irritation when tested with 100% Carbomer. Clinical studies with Carbomer and its various salts showed low potential for skin irritation and sensitization at concentrations of 0.5%, 5%, 10%, and 100%. When tested on humans at 1.0% concentration, Carbomer and its various salts also demonstrated low potential for skin irritation and sensitization.

Further, formulations containing up to 0.25% Carbomer demonstrated low potential for human skin irritation, sensitization, phototoxicity, and photo-contact allergenicity.

The dermal irritation and sensitization studies summarized here are described in Table 8; details were not available for many of the studies. In animal studies, Acrylates/Beheneth-25 Methacrylate Copolymer¹⁰ and Acrylates/Hydroxyesters Acrylates Copolymer (in a product containing < 50%)¹⁴ were classified as slightly irritating to rabbit skin. Acrylates Copolymer^{13,15} and VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol⁸ were not irritating to rabbit skin. Acrylates Copolymer was not classified as a sensitizer in a local lymph node assay (LLNA),¹³ or in a Buehler test using guinea pigs.¹⁵ VA/Butyl Maleate/Isobornyl Acrylate Copolymer (as a slurry in ethanol) produced slight erythema in 20% of the 25 subjects tested in a 48-h patch test.⁸ In an HRIPT, Acrylates/Hydroxyesters Acrylates Copolymer (as a product containing < 50%) was not a sensitizer, and it was concluded that VA/Butyl Maleate/Isobornyl Acrylate Copolymer in 10% ethanol not likely to be a sensitizer (109 subjects); erythema was observed in a few subjects at both induction and challenge.⁸

Phototoxicity/Photosensitization

Human

VA/Butyl Maleate/Isobornyl Acrylate Copolymer

The phototoxicity of VA/Butyl Maleate/Isobornyl Acrylate Copolymer was evaluated in 10 fair-skinned subjects.⁸ Patches with 0.2 ml of the copolymer in 10% ethanol were applied to both volar forearms of each subject for 24 h. One arm was irradiated with ultraviolet A (UVA) for 15 minutes (total dose = 3.3 J); an untested site on this arm served as an irradiated control. The other arm was not irradiated and was protected from light, including sunlight, by either a mitten or a long sleeve. Immediately after irradiation and at 48 and 72 h, both arms were graded for reactions. Minimal erythema at the test site, which occurred immediately after irradiation, was observed in one subject; no other reactions were reported. It was concluded that the test article "is not likely to be phototoxic in humans" at the concentration tested.

In a photosensitization study, 24-h patches applied with 0.2 ml of VA/Butyl Maleate/Isobornyl Acrylate Copolymer in 10% ethanol were applied to both volar forearms of 28 fair-skinned subjects twice a week for 3 wks.⁸ At 24 hours, the test sites of both arms were examined and graded. One arm was then irradiated with ultraviolet UVA for 15 minutes, followed by UVB. The dose of UVB irradiation administered was determined separately for each subject and was based on skin type and the minimal erythema dose (MED), which was established on the control arm prior to the first irradiation. The MED used in the study was set at the lesser of either the time that was sufficient to achieve a 1.0 score, or 120 seconds. An untreated site on the irradiated arm served as the irradiated control. Each test site was graded immediately after irradiation. The other treated arm was not irradiated. After a 2–wk non-treatment period, challenge patches were applied to previously untreated sites for 24 h, and the irradiated arm was exposed to UVA only.

During induction, transient effects such as minimal erythema, slight edema, and tanning were observed; most of the responses reported were seen at the irradiated treated and non-treated sites. No responses were reported on the non-irradiated arm. Following challenge, 3 subjects exhibited positive responses on the treated and irradiated arm, including minimal erythema, slight edema, skin dryness, or a combination of these symptoms. Two of these subjects also showed similar symptoms on the treated but non-irradiated arm. No reactions were observed on the non-treated irradiated forearm. It was concluded that VA/Butyl Maleate/ Isobornyl Acrylate Copolymer in 10% ethanol was "not likely to be photoallergenic or photosensitizing."

OCULAR IRRITATION STUDIES

From the Original Safety Assessment of Acrylates Copolymers¹

In two chorioallantoic membrane vascular assays (CAMVAs), Acrylates Copolymer was predicted to be non-irritating, and in two bovine corneal opacity and permeability (BCOP) test, it was predicted to be a mild irritant. In ocular irritation studies using rabbits, Acrylates Copolymer was generally non- to mildly irritating. In two other studies, Acrylates Copolymer was an eye irritant but not corrosive. A mixture containing 30% Ammonium Acrylates Copolymer was practically nonirritating. An aqueous emulsion of the ammonium salt of an Ethylene/Acrylic Acid polymer produced trace corneal injury. Acrylates/VA Copolymer produced severe but reversible ocular irritation, and Vinyl Acetate/Maleate/ Acrylate Copolymer solution produced moderate to severe but reversible ocular irritation. In a Draize eye test, the greatest tolerated concentration of Sodium Polyacrylate was 13% to 20% and 20% to 30% for unrinsed and rinsed eyes, respectively. In an irritant threshold test, the greatest concentration of Sodium Polyacrylate that did not produce irritation in three or more of five rabbits was 2%.

From the Safety Assessment of Crosslinked Alkyl Acrylates²

Alternative test methods for ocular irritation indicated that Acrylates/Vinyl Isodecanoate Crosspolymer and a formulation containing 1% lauryl Methacrylate/Glycol Dimethacrylate Crosspolymer are not likely ocular irritants. In studies using rabbits, undiluted Acrylates/C10-30 Alkyl Acrylate Crosspolymer produced minimal to moderate irritation, and it was considered a borderline irritant in unrinsed rabbit eyes. Acrylates Crosspolymer, at 50% in olive oil, and Sodium Acrylates Crosspolymer 2 did not appear to be ocular irritants in rabbit eyes.

From the Safety Assessment of PMMA and related ingredients³

In an EpiOcular test, PMMA had a Draize ocular irritation score of 0. PMMA was mildly irritating in rabbit eyes.

From the Safety Assessment of [Carbomer]⁴

Rabbits showed zero to moderate eye irritation when tested with Carbomer and/or its various salts at concentrations of 0.20 - 100%.

The ocular irritation studies summarized here are described in Table 9. All of the studies were performed in rabbits; details were not available for several of the studies. Acrylates Copolymer was not an ocular irritant in one study, ¹⁵ and was slightly irritating in another.¹³ Acrylates/Beheneth-25 Methacrylate Copolymer¹⁰ and Acrylates/Hydroxyesters Acrylates Copolymer (as a product containing < 50%)¹⁴ were slightly irritating to rabbit eyes, and VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol (tested undiluted) was a moderate to severe eye irritant.⁸

CLINICAL STUDIES

Occupational Exposure

From the Original Safety Assessment of Acrylates Copolymers¹

In examining the effects of workplace exposures, employees exposed to a variety of acrylic polymer dusts (as well as other materials) did not have an excess of chest x-ray abnormalities, especially those suggestive of diffuse pulmonary fibrosis. Additionally, they did not have an excess of pulmonary function testing (PFT) abnormality.

Risk Assessment

From the Safety Assessment of Crosslinked Alkyl Acrylates²

Two different risk assessments evaluating the carcinogenic endpoint for benzene that may be present in Acrylates/C10-30 Alkyl Acrylates Crosspolymer resulted in different lifetime risk. One found that the risk was within the range associated with a 10^6 cancer risk, while the other reported a 20-fold greater risk.

SUMMARY

The Panel has previously issued a Final Report on Acrylates Copolymer and 33 Related Cosmetic Ingredients in 2002, concluding that the acrylates copolymers named in that report are safe for use in cosmetics when formulated to avoid irritation. The Panel also reviewed the safety of numerous similar ingredients in several other reports. The Panel determined that it is appropriate to include all the copolymers in one assessment, including crosslinked copolymers (i.e., crosspolymers)) prepared from monomers that comprise, in part, acrylic acid and/or methacrylic acid; the methyl, ethyl, propyl, or butyl ester(s) of these acids; or the salts of one or both of these two acids. Additionally, the Panel determined that three acrylates copolymers that were included in the original report should be excluded here because these are already under review in a concurrent safety assessment. As a result, this is a safety assessment of 126 ingredients similar copolymers that are commonly reported to function as film formers and viscosity increasing agents.

According to FDA VCRP data and the results of the Council use survey, 66 of the 126 ingredients assessed in this report are in use. According to VCRP data, Carbomer has the highest frequency of use; it is reported to be used in 6434 cosmetic formulations, and most of these uses (5336) are in leave-on products. Acrylates Copolymer and Acrylate/C10-30 Alkyl Acrylate Crosspolymer (solvent not specified) also have very high frequency of use, with 3177 and 3135 reported uses, respectively.

The results of concentration of use surveys conducted by the Council in 2018 indicate that Acrylates Copolymer has the highest maximum use concentration; it is used at up to 98.6% in nail extenders; use in product categories other than nail products is not as high, but Acrylates Copolymer is used at up to 25% in products that result in dermal contact (face and neck products). Ingredients with the next highest reported concentrations of use are Acrylates/VA Copolymer (at 50%, in "other" skin care formulations) and Polymethyl Methacrylate (at up to 44.6%, in face powders).

In ADME studies of Acrylates Copolymer (either as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate or as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid), most of the test substance was excreted in the feces. Very little radioactivity was recovered in the urine or in the carcass.

Dermal LD₅₀s of > 2 g/kg and > 5 g/kg were reported for Acrylates Copolymer in rats, and in rabbits, an LD₅₀ of > 2 g/kg was reported for VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol. The dermal LD₅₀s of Acrylates/ Beheneth-25 Methacrylate Copolymer and Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%) in rats were > 5 g/kg. Acute oral studies were conducted on Acrylates Copolymer; the LD₅₀s of > 5 g/kg were reported for Acrylates/Beheneth-25 Methacrylate Sopolymer/kg bw, respectively. In oral studies in rats, LD₅₀s of > 5 g/kg were reported for Acrylates/Beheneth-25 Methacrylate Copolymer, Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%), and VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol. For Polyacrylate-1 Crosspolymer, the oral LD₅₀ in rats was > 2 g/kg. In a acute inhalation study of Acrylates Copolymer in rats, the LC₅₀ was > 3960 mg/l.

In a gavage study, rats were dosed with 500, 1000, and 2000 mg/kg bw/day of dry Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) for 35 days. There were no notable findings, and the NOAEL was 2000 mg/kg bw/day. In a 28-day dietary study in which rats were fed Acrylates Copolymer-coated cellulose pellets at a dose up to 2000 mg/kg bw/d. There were no toxicologically relevant changes in body weight, food consumption, clinical observations,

ophthalmoscopy, clinical pathology, urinalysis, fecal analysis, or in organ weights. In this study, the NOAEL was determined to be 227 mg dry copolymer/kg bw/d. In similar studies in which rats and dogs were fed Acrylates Copolymer-coated pellets for 26 weeks, the NOAEL was \geq 2000 mg dry copolymer/kg bw/day for rats, and it was determined to be 250 mg dry copolymer/kg bw/d for dogs. These were the highest doses tested in the 26 wk studies.

In two dietary studies in which an Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate) dispersion was sprayed onto powdered diet and administered at a dose up to 2000 mg dry copolymer/kg bw/day and fed to pregnant rats (on days 6 - 15 of gestation) and rabbits (on days 6 - 18 of gestation), there were no signs of maternal toxicity in rats or rabbits, and there were no reproductive or developmental effects observed for either species. The NOAELs for dams and fetuses were 2000 mg/kg bw/day in both rats and rabbits.

Acrylates Copolymer (comprised of various monomer combinations) was not genotoxic in Ames tests (up to 5000 μ g dry copolymer/plate), mouse lymphoma L5178Y cell mutation assays (up to 6250 μ g dry copolymer/ml), or a chromosomal aberration assay (up to 9000 μ g dry copolymer/ml in human lymphocytes), and it was not genotoxic in the mouse micronucleus test in which mice were dosed with up to 2000 mg dry copolymer/kg bw. Acrylates/Hydroxyesters Acrylates Copolymer (in a product containing < 50%) also was not mutagenic in the Ames test.¹⁴ Details were not available for many of these studies.

Carcinogenicity data were neither found in the published in the publically available literature, nor were unpublished studies submitted. However, in 2013, "polyacrylates" was nominated to the NTP Report on Carcinogens.

In animal studies, Acrylates/Beheneth-25 Methacrylate Copolymer and Acrylates/Hydroxyesters Acrylates Copolymer (in a product containing < 50%) were classified as slightly irritating to rabbit skin. Acrylates Copolymer and VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol were not irritating to rabbit skin. Acrylates Copolymer was not classified as a sensitizer in a LLNA, or in a Buehler test using guinea pigs. VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol, tested neat, was not irritating or sensitizing in a Buehler test in guinea pigs. In clinical testing, VA/Butyl Maleate/Isobornyl Acrylate Copolymer (as a slurry in ethanol) produced slight erythema in 20% of the 25 subjects tested in a 48-h patch test. In an HRIPT, Acrylates/Hydroxyesters Acrylates Copolymer (as a product containing < 50%) was not a sensitizer, and it was concluded that VA/Butyl Maleate/Isobornyl Acrylate Copolymer in 10% ethanol not likely to be a sensitizer (109 subjects); erythema was observed in a few subjects at both induction and challenge.

In study in which the phototoxicity of VA/Butyl Maleate/Isobornyl Acrylate Copolymer in 10% ethanol was evaluated in 10 fair-skinned subjects following 24 h patches, it was concluded that the test article "is not likely to be phototoxic in humans." In a similar test in which 24-h patches were applied to 28 fair-skinned subjects twice a week for 3 wks, VA/Butyl Maleate/Isobornyl Acrylate Copolymer in 10% ethanol was "not likely to be photoallergenic or photosensitizing."

Ocular irritation studies were performed in rabbits; details were not available for several of the studies. Acrylates Copolymer was not an ocular irritant in one study, and was slightly irritating in another. Acrylates/Beheneth-25 Methacrylate Copolymer and Acrylates/Hydroxyesters Acrylates Copolymer (as a product containing < 50%) were slightly irritating to rabbit eyes, and VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol (tested undiluted) was a moderate to severe eye irritant.

DISCUSSION

In accordance with its procedures, CIR evaluates the conclusions of previously-issued reports approximately every 15 years. In 2002, the Panel reviewed the safety of Acrylates Copolymer and 33 related cosmetic ingredients, and concluded that those ingredients were safe for use in cosmetics when formulated to avoid irritation. The Panel has issued three other reports on related copolymers and crosspolymer prepared from monomers that comprise, in part, acrylic acid or methacrylic acid (as well as appropriate salts and esters of these acids). In addition to those acrylates copolymers previously reviewed, the Panel determined that it was appropriate to include 70 acrylates copolymers that have not yet been reviewed. Subsequently, there are a few copolymers that fit the description for this family that are not included in this report because they were recently included in other reports, and there are some that will warrant a review of their own in in the near future because of frequency of use.

The Panel recognized the large number of ingredients in this safety assessment, and the fact that these polymers are comprised of many different monomeric building blocks. Nonetheless, these polymers are uniformly large molecules and are produced in chemical reactions that leave very little residual monomer. For these reasons, the Panel concluded that it is reasonable to consider these ingredients as a group, and the collection of these 126 ingredients in one report enables the assembly of reinforcing and complementary test data.

Acrylates Copolymer is used at up to 98.6% in nail extenders; however, concentrations of use in products that result in dermal exposure are lower (i.e., 50% or less). Because these copolymers are generally large molecules, significant dermal absorption is not expected. Therefore, topically applied cosmetics are not expected to result in systemic toxicity. Additionally, the existing data support a lack of sensitization potential; consequently, the Panel was satisfied that the data included in this report (as well as those data described in the previous reports) supported the safety of the acrylates copolymers as used in cosmetics.

The Panel discussed the concern of residual monomer that might be present in these polymers. In most cases, taking into consideration the low amount of residual monomer in the polymers, the Panel was not concerned that the presence of residual monomer would result in adverse effects. However, the Panel did stress that manufacturers should continue to use good manufacturing processes to ensure the amount of residual monomer is kept to a minimum.

The Panel also discussed the issue of residual solvent that might be present. Again, the Panel stressed that the amount of residual solvent should be minimized. However, the Panel was particularly concerned with polymerization in benzene. It cannot be predicted with certainty what quantity of benzene would be volatilized/leached from a polymer during manufacture, formulation, or use; while some benzene is inevitably volatilized during manufacture, some benzene may be trapped in the polymer matrix and may leach out during formulation and use. Because of this uncertainty, the Panel stipulated that these ingredients should not be polymerized in benzene.

The Panel remarked that the potential exists for dermal irritation with the use of products formulated using the ingredients named in this assessment. Therefore, the Panel specified that products containing the acrylates copolymers named in this assessment must be formulated to be non-irritating.

Finally, because some of the acrylates copolymers are used in cosmetic sprays and powders (e.g., VA/Butyl Maleate/Isobornyl Acrylate Copolymer is reported to be used at a maximum concentration of 10% in aerosol hair sprays and Polymethyl Methacrylate is used at concentrations up to 44.6% in face powders) and could possibly be inhaled, the Panel discussed the issue of potential inhalation toxicity. As discussed in the initial assessment on Acrylates Copolymer, the acrylic acid monomer can be a nasal irritant; however, exposure to the monomer from use of these polymers in cosmetic formulations would be less than the established threshold limit value for nasal irritation. Also, the Panel noted that in aerosol products, 95% – 99% of droplets/particles would not be respirable to any appreciable amount. Furthermore, droplets/particles deposited in the nasopharyngeal or bronchial regions of the respiratory tract present no toxicological concerns based on the chemical and biological properties of these ingredients. Coupled with the small actual exposure in the breathing zone and the concentrations at which the ingredients are used, the available information indicates that incidental inhalation would not be a significant route of exposure that might lead to local respiratory or systemic effects. A detailed discussion and summary of the Panel's approach to evaluating incidental inhalation exposures to ingredients in cosmetic products is available at <u>http://www.cir-safety.org/cir-findings</u>.

CONCLUSION

The Panel issued a tentative amended report for public comment with the conclusion that the 126 acrylates copolymers named below are safe in cosmetics in the present practices of use and concentration described in the safety assessment when formulated to be non-irritating.

Acrylates Copolymer Acrylates Crosspolymer Acrylates Crosspolymer-3 Acrylates Crosspolymer-4 Acrylates Crosspolymer-5* Acrylates/Ammonium Methacrylate Copolymer Acrylates/Beheneth-25 Methacrylate Copolymer Acrylates/Beheneth-25 Methacrylate/Steareth-30 Methacrylate Copolymer* Acrylates/C10-30 Alkyl Methacrylate Copolymer Acrylates/C10-30Alkyl Acrylate Crosspolymer Acrylates/C12-13 Alkyl Methacrylates/Methoxyethyl Acrylate Crosspolymer* Acrylates/C12-22 Alkyl Methacrylate Copolymer Acrylates/C26-28 Olefin Copolymer* Acrylates/C5-8 Alkyl Acrylate Copolymer* Acrylates/Ceteareth-20 Methacrylate Crosspolymer* Acrylates/Ceteareth-20 Methacrylate Crosspolymer-2* Acrylates/Ceteth-20 Methacrylate Copolymer* Acrylates/Ethylhexyl Acrylate Copolymer Acrylates/Ethylhexyl Acrylate Crosspolymer Acrylates/Ethylhexyl Acrylate/Glycidyl Methacrylate Crosspolymer* Acrylates/Hydroxyesters Acrylates Copolymer Acrylates/Hydroxyethyl Acrylate/Lauryl Acrylate Copolymer* Acrylates/Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer* Acrylates/Laureth-25 Methacrylate Copolymer* Acrylates/Lauryl Methacrylate Copolymer* Acrylates/Lauryl Methacrylate/Tridecyl Methacrylate Crosspolymer* Acrylates/Methoxy PEG-4 Methacrylate Copolymer*

Acrylates/Methoxy PEG-15 Methacrylate Copolymer* Acrylates/Methoxy PEG-23 Methacrylate Copolymer Acrylates/Methoxy PEG-90 Methacrylate Crosspolymer* Acrylates/Palmeth-25 Acrylate Copolymer Acrylates/PEG-4 Dimethacrylate Crosspolymer* Acrylates/Steareth-20 Methacrylate Copolymer Acrylates/Steareth-20 Methacrylate Crosspolymer Acrylates/Steareth-30 Methacrylate Copolymer Acrylates/Steareth-50 Acrylate Copolymer* Acrylates/Stearyl Methacrylate Copolymer Acrylates/VA Copolymer Acrylates/VA Crosspolymer Acrylates/Vinyl Isodecanoate Crosspolymer Acrylates/Vinyl Neodecanoate Crosspolymer Acrylic Acid/C12-22 Alkyl Acrylate Copolymer* Acrylic Acid/Stearyl Acrylate Copolymer Allyl Methacrylate/Glycol Dimethacrylate Crosspolymer* Allyl Methacrylates Crosspolymer Ammonium Acrylates Copolymer Ammonium Acrylates/Ethylhexyl Acrylate Copolymer* Ammonium Acrylates/Methyl Styrene/Styrene Copolymer Ammonium Polyacrylate Ammonium Styrene/Acrylates Copolymer Ammonium Styrene/Acrylates/Ethylhexyl Acrylate/Lauryl Acrylate Copolymer* Ammonium VA/Acrylates Copolymer* AMP-Acrylates Copolymer Behenyl Methacrylate/t-Butyl Methacrylate Copolymer Butyl Acrylate/Cyclohexyl Methacrylate Copolymer* Butyl Acrylate/Ethylhexyl Methacrylate Copolymer* Butyl Acrylate/Glycol Dimethacrylate Crosspolymer Butyl Acrylate/Hydroxyethyl Methacrylate Copolymer* Butyl Methacrylate/Acryoyloxy PG Methacrylate Copolymer*

C12-22 Alkyl Acrylate/Hydroxyethylacrylate Copolymer C8-22 Alkyl Acrylates/Methacrylic Acid Crosspolymer* Calcium Potassium Carbomer* Carbomer Cyclohexyl Methacrylate/Ethylhexyl Methacrylate Copolymer* Ethylene/Acrylic Acid Copolymer Ethylene/Acrylic Acid/VA Copolymer* Ethylene/Calcium Acrylate Copolymer* Ethylene/Magnesium Acrylate Copolymer* Ethylene/Methacrylate Copolymer Ethylene/Sodium Acrylate Copolymer Ethylene/Zinc Acrylate Copolymer* Ethylhexyl Acrylate/Methoxy PEG-23 Methacrylate/Vinyl Acetate Copolymer* Ethylhexyl Acrylate/Methyl Methacrylate Copolymer Glycol Dimethacrylate Crosspolymer* Glycol Dimethacrylate/Vinyl Alcohol Crosspolymer* Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer* Lauryl Acrylate Crosspolymer Laurvl Acrvlate/VA Copolymer* Lauryl Acrylate/VA Crosspolymer* Lauryl Methacrylate/Glycol Dimethacrylate Crosspolymer Lauryl Methacrylate/Sodium Methacrylate Crosspolymer Methacrylic Acid/PEG-6 Methacrylate/PEG-6 Dimethacrylate Crosspolymer* Methacryloyl Ethyl Betaine/Acrylates Copolymer Methoxy PEG-23 Methacrylate/Glyceryl Diisostearate Methacrylate Copolymer Methyl Methacrylate Crosspolymer Methyl Methacrylate/Glycol Dimethacrylate Crosspolymer Methyl Methacrylate/PEG/PPG-4/3 Methacrylate Crosspolymer PEG/PPG-5/2 Methacrylate/Methacrylic Acid Crosspolymer* Poly C10-30 Alkyl Acrylate Poly(Methoxy PEG-9 Methacrylate)*

Polyacrylate-14 Polyacrylate-29* Polyacrylate-34* Polyacrylate-1 Crosspolymer Polyacrylic Acid Polybutyl Acrylate* Polybutyl Methacrylate* Polyethylacrylate Polyhydroxyethylmethacrylate* Polyisobutyl Methacrylate* Polymethyl Acrylate Polymethyl Methacrylate Polypropyl Methacrylate* Polystearyl Methacrylate* Potassium Acrylate Crosspolymer* Potassium Acrylates Copolymer Potassium Acrylates/C10-30 Alkyl Acrylate Crosspolymer Potassium Acrylates/Ethylhexyl Acrylate Copolymer* Potassium Aluminum Polyacrylate* Potassium Carbomer Potassium Polvacrvlate* Sodium Acrylate/Acrolein Copolymer* Sodium Acrylate/Vinyl Alcohol Copolymer Sodium Acrylates Copolymer Sodium Acrylates Crosspolymer-2 Sodium Acrylates/Beheneth-25 Methacrylate Crosspolymer* Sodium Acrylates/C10-30 Alkyl Acrylate Crosspolymer Sodium Acrylates/Ethylhexyl Acrylate Copolymer* Sodium Acrylates/Vinyl Isodecanoate Crosspolymer Sodium Carbomer Sodium Polyacrylate Sodium Polymethacrylate Steareth-10 Allyl Ether/Acrylates Copolymer Stearyl/Lauryl Methacrylate Crosspolymer* Styrene/Acrylates/Ammonium Methacrylate Copolymer VA/Butyl Maleate/Isobornyl Acrylate Copolymer

*Not reported to be in current use. Were ingredients in this group not in current use to be used in the future, the expectation is that they would be used in product categories and at concentrations comparable to others in this group.

TABLES

Table 1. List of 126 ingredients included in this re-review Acrylates Copolymer Acrylates Crosspolymer Acrylates Crosspolymer-3 Acrylates Crosspolymer-4 Acrylates Crosspolymer-5 Acrylates/Ammonium Methacrylate Copolymer Acrylates/Beheneth-25 Methacrylate Copolymer Acrylates/Beheneth-25 Methacrylate/Steareth-30 Methacrylate Copolymer Acrylates/C10-30 Alkyl Methacrylate Copolymer Copolymer Acrylates/C10-30Alkyl Acrylate Crosspolymer Acrylates/C12-13 Alkyl Methacrylates/Methoxyethyl Acrylate Crosspolymer Acrylates/C12-22 Alkyl Methacrylate Copolymer Acrylates/C26-28 Olefin Copolymer Acrylates/C5-8 Alkyl Acrylate Copolymer Acrylates/Ceteareth-20 Methacrylate Crosspolymer Acrylates/Ceteareth-20 Methacrylate Crosspolymer-2 Acrylates/Ceteth-20 Methacrylate Copolymer Acrylates/Ethylhexyl Acrylate Copolymer Acrylates/Ethylhexyl Acrylate Crosspolymer Acrylates/Ethylhexyl Acrylate/Glycidyl Methacrylate Crosspolymer Acrylates/Hydroxyesters Acrylates Copolymer Acrylates/Hydroxyethyl Acrylate/Lauryl Acrylate Copolymer Copolymer Acrylates/Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer Acrylates/Laureth-25 Methacrylate Copolymer Acrylates/Lauryl Methacrylate Copolymer Acrylates/Lauryl Methacrylate/Tridecyl Methacrylate Crosspolymer Acrylates/Methoxy PEG-4 Methacrylate Copolymer Acrylates/Methoxy PEG-15 Methacrylate Copolymer Acrylates/Methoxy PEG-23 Methacrylate Copolymer Polyacrylate-14 Acrylates/Methoxy PEG-90 Methacrylate Crosspolymer Polyacrylate-29 Acrylates/Palmeth-25 Acrylate Copolymer Polyacrylate-34 Acrylates/PEG-4 Dimethacrylate Crosspolymer Acrylates/Steareth-20 Methacrylate Copolymer Polyacrylic Acid Acrylates/Steareth-20 Methacrylate Crosspolymer Polybutyl Acrylate Acrylates/Steareth-30 Methacrylate Copolymer Acrylates/Steareth-50 Acrylate Copolymer Polyethylacrylate Acrylates/Stearyl Methacrylate Copolymer Acrylates/VA Copolymer Acrylates/VA Crosspolymer Acrylates/Vinyl Isodecanoate Crosspolymer Acrylates/Vinyl Neodecanoate Crosspolymer Acrylic Acid/C12-22 Alkyl Acrylate Copolymer Acrylic Acid/Stearyl Acrylate Copolymer Allyl Methacrylate/Glycol Dimethacrylate Crosspolymer Allyl Methacrylates Crosspolymer Ammonium Acrylates Copolymer Ammonium Acrylates/Ethylhexyl Acrylate Copolymer Ammonium Acrylates/Methyl Styrene/Styrene Copolymer Ammonium Polyacrylate Ammonium Styrene/Acrylates Copolymer Ammonium Styrene/Acrylates/Ethylhexyl Acrylate/Lauryl Acrylate Copolymer Ammonium VA/Acrylates Copolymer AMP-Acrylates Copolymer Behenyl Methacrylate/t-Butyl Methacrylate Copolymer Butyl Acrylate/Cyclohexyl Methacrylate Copolymer Butyl Acrylate/Ethylhexyl Methacrylate Copolymer Sodium Carbomer Butyl Acrylate/Glycol Dimethacrylate Crosspolymer Butyl Acrylate/Hydroxyethyl Methacrylate Copolymer Butyl Methacrylate/Acryoyloxy PG Methacrylate Copolymer C12-22 Alkyl Acrylate/Hydroxyethylacrylate Copolymer C8-22 Alkyl Acrylates/Methacrylic Acid Crosspolymer Calcium Potassium Carbomer VA/Butyl Maleate/Isobornyl Acrylate Copolymer Carbomer Cyclohexyl Methacrylate/Ethylhexyl Methacrylate Copolymer

Ethylene/Acrylic Acid Copolymer Ethylene/Acrylic Acid/VA Copolymer Ethylene/Calcium Acrylate Copolymer Ethylene/Magnesium Acrylate Copolymer Ethylene/Methacrylate Copolymer Ethylene/Sodium Acrylate Copolymer Ethylene/Zinc Acrylate Copolymer Ethylhexyl Acrylate/Methoxy PEG-23 Methacrylate/Vinyl Acetate Ethylhexyl Acrylate/Methyl Methacrylate Copolymer Glycol Dimethacrylate Crosspolymer Glycol Dimethacrylate/Vinyl Alcohol Crosspolymer Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer Lauryl Acrylate Crosspolymer Lauryl Acrylate/VA Copolymer Lauryl Acrylate/VA Crosspolymer Lauryl Methacrylate/Glycol Dimethacrylate Crosspolymer Lauryl Methacrylate/Sodium Methacrylate Crosspolymer Methacrylic Acid/PEG-6 Methacrylate/PEG-6 Dimethacrylate Crosspolymer Methacryloyl Ethyl Betaine/Acrylates Copolymer Methoxy PEG-23 Methacrylate/Glyceryl Diisostearate Methacrylate Methyl Methacrylate Crosspolymer Methyl Methacrylate/Glycol Dimethacrylate Crosspolymer Methyl Methacrylate/PEG/PPG-4/3 Methacrylate Crosspolymer PEG/PPG-5/2 Methacrylate/Methacrylic Acid Crosspolymer Poly C10-30 Alkyl Acrylate Poly(Methoxy PEG-9 Methacrylate) Polyacrylate-1 Crosspolymer Polybutyl Methacrylate Polyhydroxyethylmethacrylate Polyisobutyl Methacrylate Polymethyl Acrylate Polymethyl Methacrylate Polypropyl Methacrylate Polystearyl Methacrylate Potassium Acrylate Crosspolymer Potassium Acrylates Copolymer Potassium Acrylates/C10-30 Alkyl Acrylate Crosspolymer Potassium Acrylates/Ethylhexyl Acrylate Copolymer Potassium Aluminum Polyacrylate Potassium Carbomer Potassium Polyacrylate Sodium Acrylate/Acrolein Copolymer Sodium Acrylate/Vinyl Alcohol Copolymer Sodium Acrylates Copolymer Sodium Acrylates Crosspolymer-2 Sodium Acrylates/Beheneth-25 Methacrylate Crosspolymer Sodium Acrylates/C10-30 Alkyl Acrylate Crosspolymer Sodium Acrylates/Ethylhexyl Acrylate Copolymer Sodium Acrylates/Vinyl Isodecanoate Crosspolymer Sodium Polyacrylate Sodium Polymethacrylate Steareth-10 Allyl Ether/Acrylates Copolymer Stearyl/Lauryl Methacrylate Crosspolymer Styrene/Acrylates/Ammonium Methacrylate Copolymer

Ingredients in blue type were included in the original Safety Assessment of Acrylates Copolymer and 33 Related Cosmetic Ingredients¹ Ingredients in green type were reviewed in the Safety Assessment of Cross-Linked Alkyl Acrylates² Ingredients in pink type were reviewed in the safety assessment of Polymethyl Methacrylate and other ingredients³ The ingredient in gray type was reviewed in the safety assessment of Carbomers

Prior to this assessment, the ingredients in black type had not yet been reviewed by CIR

Table 2.	Definitions, Structures, and Functions of the ingredients reviewed in this report ⁵	

Ingredients (CAS Nos.)*	Definitions and Structures	Function(s)
Acrylates Copolymer 159666-35-0; 25035-69-2; 25212-88-8; 25685-29-4	a copolymer of two or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	adhesives; artificial nail builders; binders; dispersing agents - nonsurfactant; film formers; hair fixatives; skin-conditioning agents - emollient; skin-conditioning agents - miscellaneous
Acrylates Crosspolymer 26794-61-6; 74464-10-1	a copolymer of acrylic acid, methacrylic acid or one of its simple esters, crosslinked with glycol dimethacrylate	absorbents
Acrylates Crosspolymer-3	a copolymer of acrylic acid, methacrylic acid or one of its simple esters, crosslinked with trimethylolpropane triacrylate and trimethylolpropane diallyl ether	film formers; hair fixatives; viscosity increasing agents - aqueous
Acrylates Crosspolymer-4	a copolymer of acrylic acid, methacrylic acid or one of its simple esters, crosslinked with trimethylolpropane triacrylate	emulsion stabilizers; film formers; surfactants - dispersing agents; viscosity increasing agents - aqueous
Acrylates Crosspolymer-5	a copolymer of acrylic acid, methacrylic acid or one of their simple esters, crosslinked with an allyl ether of pentaerythritol	viscosity increasing agents - aqueous
Acrylates/Ammonium Methacrylate Copolymer	a copolymer of ammonium methacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	binders; film formers; hair fixatives
Acrylates/Beheneth-25 Methacrylate Copolymer	a copolymer of the ester of methacrylic acid and Beheneth-25 and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/Beheneth-25 Methacrylate/Steareth-30 Methacrylate Copolymer	a copolymer of beheneth-25 methacrylate, steareth-30 methacrylate and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	film formers
Acrylates/C10-30 Alkyl Methacrylate Copolymer	the copolymer of C10-30 alkyl methacrylate and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/C10-30Alkyl Acrylate Crosspolymer	a copolymer of C10-30 alkyl acrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters crosslinked with an allyl ether of sucrose or an allyl ether of pentaerythritol	emulsion stabilizers; viscosity increasing agents - aqueous; viscosity increasing agents - nonaqueous
Acrylates/C12-13 Alkyl Methacrylates/Methoxy- ethyl Acrylate Crosspolymer	a copolymer of C12-13 alkyl methacrylates, methoxyethyl acrylate, and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters, crosslinked with vinyloxazoline	hair fixatives
Acrylates/C12-22 Alkyl Methacrylate Copolymer	the copolymer of C12-22 alkyl methacrylate and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters	film formers
Acrylates/C26-28 Olefin Copolymer	a polymer of C26-28 olefins and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	viscosity increasing agents - nonaqueous
Acrylates/C5-8 Alkyl Acrylate Copolymer	copolymer of C5-8 alkyl acrylate and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters	emulsion stabilizers; film formers; viscosity increasing agents - aqueous
Acrylates/Ceteareth-20 Methacrylate Crosspolymer	copolymer of the ester of methacrylic acid and Ceteareth-20 and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters, crosslinked with ethylene glycol dimethacrylate	viscosity increasing agents - aqueous
Acrylates/Ceteareth-20 Methacrylate Crosspolymer-2	a copolymer of the ester of methacrylic acid and ceteareth-20 and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters, crosslinked with diallyl maleate	bulking agents; chelating agents; emulsion stabilizers; opacifying agents; viscosity increasing agents - aqueous
Acrylates/Ceteth-20 Methacrylate Copolymer	a copolymer formed from the ester of methacrylic acid and ceteth-20, and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/Ethylhexyl Acrylate Copolymer	a copolymer of ethylhexyl acrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	film formers
Acrylates/Ethylhexyl Acrylate Crosspolymer	a copolymer of 2-ethylhexylacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters, crosslinked with ethylene glycol dimethacrylate	binders
Acrylates/Ethylhexyl Acrylate/Glycidyl Methacrylate Crosspolymer	a copolymer of 2-ethylhexyl acrylate, glycidyl methacrylate and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters, crosslinked with triethylene glycol dimethacrylate	film formers

Table 2. Definitions, Structures, and Functions of the ingredients reviewed in this report⁵

Ingredients (CAS Nos.)*	Definitions and Structures	Function(s)
Acrylates/Hydroxyesters Acrylates Copolymer 25035-89-6	a copolymer of one or more monomers consisting of acrylic acid, methacrylic acid, or their simple esters, and one or more monomers of hydroxyacrylate esters	film formers
Acrylates/Hydroxyethyl Acrylate/Lauryl Acrylate Copolymer	a copolymer of hydroxyethyl acrylate, lauryl acrylate, and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	film formers
Acrylates/Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer	a copolymer of hydroxyethyl acrylate, butyl acrylate and methoxyethyl acrylate	film formers
Acrylates/Laureth-25 Methacrylate Copolymer	the copolymer of laureth-25 methacrylate and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/Lauryl Methacrylate Copolymer	a copolymer of lauryl methacrylate and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	film formers
Acrylates/Lauryl Methacrylate/Tridecyl Methacrylate Crosspolymer	a copolymer of lauryl methacrylate, tridecyl methacrylate and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters, crosslinked with vinyloxazoline	film formers
Acrylates/Methoxy PEG-4 Methacrylate Copolymer	a copolymer of methoxy PEG-4 methacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	hair conditioning agents
Acrylates/Methoxy PEG-15 Methacrylate Copolymer	a copolymer of methoxy PEG-15 methacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	dispersing agents - nonsurfactant
Acrylates/Methoxy PEG-23 Methacrylate Copolymer	a copolymer of methoxy PEG-23 methacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	film formers
Acrylates/Methoxy PEG-90 Methacrylate Crosspolymer 957645-61-3	a copolymer of methoxy PEG-90 methacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters crosslinked by glycol dimethacrylate	skin protectants
Acrylates/Palmeth-25 Acrylate Copolymer	a copolymer of the ester of acrylic acid and ethoxylated palm alcohol with an average of 25 moles of ethylene oxide and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/PEG-4 Dimethacrylate Crosspolymer 50657-38-0	a copolymer of one or more monomers of acrylic acid, methacrylic acid or one of their simple esters crosslinked by PEG-4 dimethacrylate	film formers
Acrylates/Steareth-20 Methacrylate Copolymer	a copolymer of the ester of methacrylic acid and steareth-20 and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/Steareth-20 Methacrylate Crosspolymer	a copolymer of steareth-20 methacrylate and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters, crosslinked with an allyl ether of pentaerythritol or an allyl ether of trimethylolpropane	dispersing agents - nonsurfactant; film formers
Acrylates/Steareth-30 Methacrylate Copolymer 75760-37-1	a copolymer of the ester of methacrylic acid and steareth-30 and one or more monomers of acrylic acid, methacrylic acid, or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/Steareth-50 Acrylate Copolymer	a copolymer of the ester of acrylic acid and steareth-50 and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	viscosity increasing agents - aqueous
Acrylates/Stearyl Methacrylate Copolymer	a copolymer of stearyl methacrylate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	emulsion stabilizers; viscosity increasing agents - aqueous
Acrylates/VA Copolymer	a copolymer of vinyl acetate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters	binders; film formers; hair fixatives
Acrylates/VA Crosspolymer	a copolymer of vinyl acetate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters crosslinked with triallylisocyanurate	film formers
Acrylates/Vinyl Isodecanoate Crosspolymer	a copolymer of the ester of vinyl isodecanoate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters crosslinked with polyalkenyl polyether	dispersing agents - nonsurfactant; emulsion stabilizers; viscosity increasing agents - aqueous
Acrylates/Vinyl Neodecanoate Crosspolymer	a copolymer of vinyl neodecanoate and one or more monomers of acrylic acid, methacrylic acid or one of their simple esters crosslinked with an allyl ether of trimethylolpropane or pentaerythritol	emulsion stabilizers; film formers; viscosity increasing agents - aqueous
Acrylic Acid/C12-22 Alkyl Acrylate Copolymer	a copolymer of acrylic acid and C12-22 alkyl acrylate	binders; emulsion stabilizers; viscosity increasing agents - nonaqueous

 Table 2. Definitions, Structures, and Functions of the ingredients reviewed in this report⁵

Ingredients (CAS Nos.)*	Definitions and Structures	Function(s)
Acrylic Acid/Stearyl Acrylate Copolymer 36120-03-3	a polymer of acrylic acid and stearyl acrylate monomers	emulsion stabilizers; film formers; surfactants - emulsifying agents
Allyl Methacrylate/Glycol Dimethacrylate Crosspolymer 779327-42-3	a highly crosslinked polymer of allyl methacrylate and ethylene glycol dimethacrylate	oral care agents; skin protectants; skin-conditioning agents - emollient; skin-conditioning agents - miscellaneous
Allyl Methacrylates Crosspolymer 182212-41-5	a copolymer of allyl methacrylates crosslinked with glycol dimethacrylate	emulsion stabilizers; opacifying agents; viscosity increasing agents - nonaqueous
Ammonium Acrylates Copolymer	the ammonium salt of a polymer of two or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	binders; film formers; viscosity increasing agents - aqueous
Ammonium Acrylates/Ethylhexyl Acrylate Copolymer	a copolymer of ethylhexyl acrylate and the ammonium salt of one or more monomers consisting of acrylic acid, methacrylic acid, or one of their simple esters	film formers
Ammonium Acrylates/Methyl Styrene/Styrene Copolymer	a copolymer consisting of ammonium acrylate, methyl styrene and styrene monomers	film formers
Ammonium Polyacrylate 9003-03-6	the ammonium salt of Polyacrylic Acid	emulsion stabilizers; film formers
Ammonium Styrene/Acrylates Copolymer	the ammonium salt of a polymer of styrene and a monomer consisting of acrylic acid, methacrylic acid or one of their simple esters	dispersing agents - nonsurfactant; film formers
Ammonium Styrene/Acrylates/Ethylhexyl Acrylate/Lauryl Acrylate Copolymer	ammonium salt of Styrene/Acrylates/Ethylhexyl Acrylate/Lauryl Acrylate Copolymer	film formers
Ammonium VA/Acrylates Copolymer	the ammonium salt of a polymer of vinyl acetate and two or more monomers consisting of acrylic acid, methacrylic acid or their simple ester	binders; dispersing agents - nonsurfactant; film formers; hair fixatives
AMP-Acrylates Copolymer 1203962-19-9	the aminomethyl propanol salt of Acrylates Copolymer	film formers
Behenyl Methacrylate/t-Butyl Methacrylate Copolymer	a copolymer of behenyl methacrylate and t-butyl methacrylate monomers	film formers
Butyl Acrylate/Cyclohexyl Methacrylate Copolymer	a copolymer of butyl acrylate and cyclohexyl methacrylate	film formers
Butyl Acrylate/Ethylhexyl Methacrylate Copolymer	a copolymer of butyl acrylate and 2-ethylhexyl methacrylate monomers	film formers; hair fixatives
Butyl Acrylate/Glycol Dimethacrylate Crosspolymer	a homopolymer of butyl acrylate crosslinked with glycol dimethacrylate	absorbents; film formers
Butyl Acrylate/Hydroxyethyl Methacrylate Copolymer	a copolymer consisting of n-butyl acrylate and 2-hydroxyethyl methacrylate monomers	film formers
Butyl Methacrylate/Acryoyloxy PG Methacrylate Copolymer 1431551-12-0	a polymer of butyl methacrylate and acryloyloxy propylene glycol methacrylate monomers	film formers
C12-22 Alkyl Acrylate/Hydroxyethylacrylate Copolymer	a copolymer of C12-22 alkyl acrylate and hydroxyethylacrylate	binders; emulsion stabilizers; viscosity increasing agents - nonaqueous
C8-22 Alkyl Acrylates/Methacrylic Acid Crosspolymer	a copolymer of C8-22 alkyl acrylate and methacrylic acid crosslinked with hexanediol diacrylate	film formers; hair fixatives; hair- waving/straightening agents
Calcium Potassium Carbomer	the calcium potassium salt of Carbomer	emulsion stabilizers; film formers; viscosity increasing agents - aqueous
Carbomer 9003-01-4; 9007-16-3; 9007-17-4; 9062-04-8; 76050-42-5	a homopolymer of acrylic acid crosslinked with an allyl ether of pentaerythritol, an allyl ether of sucrose, or an allyl ether of propylene	emulsion stabilizers; viscosity increasing agents - aqueous
Cyclohexyl Methacrylate/Ethylhexyl Methacrylate Copolymer 82227-04-1	a copolymer of cyclohexyl methacrylate and ethylhexyl methacrylate	film formers
Ethylene/Acrylic Acid Copolymer 9010-77-9	a copolymer of ethylene and acrylic acid monomers	binders; film formers; viscosity increasing agents - nonaqueous
Ethylene/Acrylic Acid/VA Copolymer 26713-18-8	a copolymer of ethylene, acrylic acid and vinyl acetate monomers	binders; film formers; viscosity increasing agents - nonaqueous
Ethylene/Calcium Acrylate Copolymer 26445-96-5	a copolymer of ethylene and calcium acrylate monomers	binders; film formers
Ethylene/Magnesium Acrylate Copolymer 27515-37-3	a copolymer of ethylene and magnesium acrylate monomers	binders; film formers
Ethylene/Methacrylate Copolymer 25103-74-6	a copolymer of ethylene and methyl methacrylate monomers	film formers
Ethylene/Sodium Acrylate Copolymer 25749-98-8; 25750-82-7	a copolymer of ethylene and sodium acrylate monomers	binders; film formers; viscosity increasing agents - aqueous

Table 2. Definitions, Structures, and Functions of the ingredients reviewed in this report⁵

Ingredients (CAS Nos.)*	Definitions and Structures	Function(s)
Ethylene/Zinc Acrylate Copolymer 28208-80-2: 59650-68-9	a copolymer of ethylene and zinc acrylate monomers	film formers
Ethylhexyl Acrylate/Methoxy PEG-23 Methacrylate/Vinyl Acetate Copolymer 137455-77-7	a copolymer of methoxy PEG-23 methacrylate, vinyl acetate, and ethylhexyl acrylate	hair fixatives
Ethylhexyl Acrylate/Methyl Methacrylate Copolymer	a copolymer of ethylhexyl acrylate and methyl methacrylate	film formers
Glycol Dimethacrylate Crosspolymer	a crosslinked polymer of glycol dimethacrylate	slip modifier
Glycol Dimethacrylate/Vinyl Alcohol Crosspolymer	a crosslinked copolymer of vinyl alcohol and glycol dimethacrylate	film formers
Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer	the copolymer of hydroxyethyl acrylate and methoxyethyl acrylate	film formers
Lauryl Acrylate Crosspolymer	a polymer of lauryl acrylate crosslinked with divinylbenzene	hair fixatives
Lauryl Acrylate/VA Copolymer	a copolymer of lauryl acrylate and vinyl acetate monomers	film formers
Lauryl Acrylate/VA Crosspolymer	a copolymer of lauryl acrylate and vinyl acetate crosslinked with divinylbenzene	abrasives
Lauryl Methacrylate/Glycol Dimethacrylate Crosspolymer	a crosslinked copolymer of lauryl methacrylate and ethylene glycol dimethacrylate monomers	film formers; hair fixatives
Lauryl Methacrylate/Sodium Methacrylate Crosspolymer	a copolymer of lauryl methacrylate and sodium methacrylate crosslinked with ethylene glycol dimethacrylate	slip modifiers; surface modifiers
Methacrylic Acid/PEG-6 Methacrylate/PEG-6 Dimethacrylate Crosspolymer	a copolymer of methacrylic acid and PEG-6 methacrylate crosslinked with PEG-6 dimethacrylate	film formers
Methacryloyl Ethyl Betaine/Acrylates Copolymer	a polymer of methacryloyl ethyl betaine and two or more monomers of methacrylic acid or its simple esters	dispersing agents - nonsurfactant; film formers; hair fixatives
Methoxy PEG-23 Methacrylate/Glyceryl Diisostearate Methacrylate Copolymer	a copolymer of methoxy PEG-23 methacrylate and glyceryl diisostearate methacrylate monomers	skin protectants
Methyl Methacrylate Crosspolymer 25777-71-3	a copolymer of methyl methacrylate crosslinked with glycol dimethacrylate	bulking agent; film former; viscosity increasing agent - nonaqueous
Methyl Methacrylate/Glycol Dimethacrylate Crosspolymer 25777-71-3	a crosslinked copolymer of methyl methacrylate and ethylene glycol dimethacrylate monomers	film formers
Methyl Methacrylate/PEG/PPG-4/3 Methacrylate Crosspolymer	a random copolymer of methyl methacrylate and PEG/PPG-4/3 methacrylate crosslinked with ethylene glycol dimethacrylate	film formers
PEG/PPG-5/2 Methacrylate/Methacrylic Acid Crosspolymer	copolymer of methacrylic acid and polyethylene glycol, polypropylene glycol methacrylate containing an average of 5 moles of ethylene oxide and 2 moles of propylene oxide, crosslinked with glycol dimethacrylate	film formers
Poly C10-30 Alkyl Acrylate	a polymer of the ester of acrylic acid and C10-30 alcohol	binders; emulsion stabilizers; viscosity increasing agents - nonaqueous
Poly(Methoxy PEG-9 Methacrylate)	the polymer that conforms generally to the formula: $ \begin{array}{c} $	film formers; skin-conditioning agents - humectant; skin-conditioning agents - occlusive
Polyacrylate-14	a copolymer of PEG-25 C10-30 alkyl ether methacrylate, PEG-20 PPG-5 allyl ether and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	film former
Polyacrylate-29	A copolymer of stearyl methacrylate, methoxy PEG-9 methacrylate and methacrylic acid	film formers; skin-conditioning agents - miscellaneous; surfactants - emulsifying agents
Polyacrylate-34	a copolymer of octoxy PEG-8 PPG-6 methacrylate, PPG-9 methacrylate, PPG-6 acrylate and 2-methoxyethylacrylate monomers	hair fixative
Polyacrylate-1 Crosspolymer	a copolymer of one or more simple esters of acrylic or methacrylic acid, C1-4 dialkylamino C1-6 alkyl methacrylate, PEG/PPG-30/5 allyl ether, PEG 20-25 C10-30 alkyl ether methacrylate, hydroxy C2-6 alkyl methacrylate crosslinked with ethylene glycol dimethacrylate	film formers; hair conditioning agents; hair fixatives; viscosity increasing agents - aqueous

Table 2. Definitions, Structures, and Functions of the ingredients reviewed in this report⁵



Table 2	Definitions	Structures on	d Functions of	f the incredies	nts reviewed in	n this report ⁵
Labic 2.	Deminions,	, ou uctur co, an	u runcuons o	i une ingreuter	no revieweu n	a uns report

Ingredients (CAS Nos.)*	Definitions and Structures	Function(s)	
Potassium Polyacrylate 25608-12-2	the potassium salt of Polyacrylic Acid	emulsion stabilizers; viscosity increasing agents - aqueous	
Sodium Acrylate/Acrolein Copolymer	a polymer consisting of sodium acrylate and acrolein monomers	binders; film formers; viscosity increasing agents - aqueous	
Sodium Acrylate/Vinyl Alcohol Copolymer 27599-56-0; 58374-38-2	a polymer of sodium acrylate and vinyl alcohol monomers	binders; emulsion stabilizers; film formers; viscosity increasing agents - aqueous	
Sodium Acrylates Copolymer 25549-84-2	the sodium salt of a polymer consisting of acrylic acid, methacrylic acid or one of their simple esters	binders; film formers; viscosity increasing agents - aqueous	
Sodium Acrylates Crosspolymer-2	the sodium salt of a copolymer of acrylic acid, methacrylic acid or one or more of its simple esters crosslinked with ethylene glycol diglycidyl ether	absorbents	
Sodium Acrylates/Beheneth-25 Methacrylate Crosspolymer	the sodium salt of a copolymer of acrylic acid, methacrylic acid or one or more of its simple esters and beheneth-25 methacrylate, crosslinked with methylene bis-acrylamide	dispersing agents - nonsurfactant; skin-conditioning agents - miscellaneous; viscosity increasing agents - aqueous	
Sodium Acrylates/C10-30 Alkyl Acrylate Crosspolymer	the sodium salt of Acrylates/C10-30 Alkyl Acrylate Crosspolymer	film formers	
Sodium Acrylates/Ethylhexyl Acrylate Copolymer	a copolymer of ethylhexyl acrylate and the sodium salt of one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	film formers	
Sodium Acrylates/Vinyl Isodecanoate Crosspolymer	the sodium salt of Acrylates/Vinyl Isodecanoate Crosspolymer	dispersing agents - nonsurfactant; emulsion stabilizers; viscosity increasing agents - aqueous	
Sodium Carbomer 1401207-41-7; 73298-57-4	sodium salt of Carbomer	emulsion stabilizers; film formers; viscosity increasing agents - aqueous	
Sodium Polyacrylate 25549-84-2; 9003-04-7	the sodium salt of Polyacrylic Acid	absorbent; emulsion stabilizer; film former; hair fixative; skin- conditioning agent - emollient; viscosity increasing agent - aqueous	
Sodium Polymethacrylate 25086-62-8; 54193-36-1	the polymer that conforms generally to the formula: $ \begin{bmatrix} CH_3 \\ I \\ CH_2C \\ I \\ COONa \end{bmatrix}_x $	binders; emulsion stabilizers; film formers; viscosity increasing agents - aqueous	
Steareth-10 Allyl Ether/Acrylates Copolymer 109292-17-3	a copolymer of the allyl ether of steareth-10 and one or more monomers consisting of acrylic acid, methacrylic acid or one of their simple esters	film formers; viscosity increasing agents - nonaqueous	
Stearyl/Lauryl Methacrylate Crosspolymer	a copolymer of stearyl methacrylate and lauryl methacrylate crosslinked with ethylene glycol dimethacrylate	skin-conditioning agents - miscellaneous	
Styrene/Acrylate/Ammonium Methacrylate Copolymer	a polymer of styrene, ammonium methacrylate and a monomer consisting of acrylic acid, methacrylic acid or one of their simple esters	dispersing agents - nonsurfactant; film formers	
VA/Butyl Maleate/Isobornyl Acrylate Copolymer	a copolymer of vinyl acetate, butyl maleate and isobornyl acrylate monomers	film formers	

*Ingredients in blue type were included in the original Safety Assessment of Acrylates Copolymer and 33 Related Cosmetic Ingredients¹ Ingredients in green type were reviewed in the Safety Assessment of Cross-Linked Alkyl Acrylates² Ingredients in pink type were reviewed in the safety assessment of Polymethyl Methacrylate and other ingredients³

The ingredient in gray type was reviewed in the safety assessment of Carbomers⁴ Prior to this assessment, the ingredients in black type had not yet been reviewed by CIR

Table 3. Physical and Chemical Properties

Property	Value	Reference
Acrylates Copolymer		
Physical Form	white beads [as 2-propenoic acid, 2-methyl-, polymer with butyl 2-methyl-2-propenoate,	13
	ethyl 2-methyl-2-propenoate and ethyl 2-propenoate]	
	liquid in commercial form; forms a film when dried	15,16
Color	milky white	15,16
Odor	"characteristic"	15,16
Molecular Weight (g/mol)	100,000 (wt avg) [as 2-propenoic acid, 2-methyl-, polymer with butyl 2-methyl-2-	13
	propenoate, ethyl 2-methyl-2-propenoate and ethyl 2-propenoate]	15
	600,000 (avg) [as a fully polymerized copolymer of methyl methacrylate and ethyl	14
	acrylate]	10
	280,000 (avg) [as a fully polymerized copolymer of methyl acrylate, methyl	
	methacrylate, and methacrylic acid	17
Density/Specific Gravity (@ 20 °C)	1.37 – 1.047 [as a fully polymerized copolymer of methyl methacrylate and ethyl	17
	acrylate	15.16
Water Solubility (g/L)	miscible in water	15,10
Acrylates/Beheneth-25 Methacrylate Copolymer	·	10
Physical Form	opaque flowing dispersion	10
Color	white	10
Melting Point (°C)	> 100	10
Water Solubility (@ $pH 2 - 3$)	insoluble	10
(@ pH 6 – 8)	soluble	
Acrylates/C12-22 Alkyl Methacrylate Copolymer	t	
Physical Form	aq. emulsion	9
Odor	acrylic	9
Water Solubility (g/L @ 20 °C)	1000	9
Acrylates/Hydroxyesters Acrylates Copolymer		
Physical Form	emulsion	33
Color	white	14
Molecular Weight (g/mol)	~ 60,000	33
Acrylates/Palmeth-25 Acrylate Copolymer	•	
Physical Form	opaque emulsion	11
Color	white	11
Water Solubility (g/L @ 20 °C)	1000	11
Acrylates/Steareth-20 Methacrylate Copolymer		
Physical Form	liquid	18
Color	milky white	18
Polyacrylate-1 Crosspolymer	•	
Physical Form	solid	12
Color	pale brown	12
Density (kg/m ³ @ 25 °C)	1160	12
Melting Point (°C)	47.35	12
VA/Butyl Maleate/Isobornyl Acrylate Copolyme	r in ethanol	
Physical Form	clear viscous liquid	8
Odor	ethanolic	8
Molecular Weight (g/mol)	79,000 – 154,000 (wt avg)	8
Vapor pressure (mmHg @ 20°C)	44.48	8
Water Solubility (g/L)	< 1; if the ethanol is allowed to evaporate, the remaining polymer is stated to be water	8
	insoluble	

Table 4. Curi	ent and historical (when	e applicable) fr	requency and concent	tration of use, accor	ding to duration and ex	posure
---------------	--------------------------	------------------	----------------------	-----------------------	-------------------------	--------

Tunto il Current una mistoria		lana	Max Come f	Line (0/)		and and	Mar Com	$f I I_{\alpha \alpha} (0/)$
	# of U	ses	Max Conc of	USE (70)	# of U	ses	Max Conc o	1 USE (%)
		Acrylat	es Copolymer			Acrylates	Crosspolymer	
	2018 ²⁴	1998 ¹	201819	1998 ¹	2018 ²⁴	2011 ²	2018 ²¹	2011 ²
Totals*	3177	227	0.00025-98.6	**	5	2	0.15-4.5	0.1-4
Duration of Use								
Leave-On	2050	207	0.00025-98.6	**	5	2	1-4.5	0.1-4
Rinse-Off	1106	20	0.00052-4.2	**	NR	NR	0.15-2.7	0.3-0.8
Diluted for (Bath) Use	21	NR	0.9-2.4	**	NR	NR	NR	NR
Exposure Type	1		1					
Eve Area	702	33	0.00025-18.4	**	1	NR	1	0.8
Incidental Ingestion	453	36	0.0003-3	**	NR	NR	NR	4
Incidental Inhalation-Spray	53: 107 ^a : 58 ^b	3. 5ª. 3b	0.36-4.9	**	1 ^a · 2 ^b	NR	NR	NR
incidental initiatation opray	55,107,50	3, 5, 5	0.30 + .9, $0.12 - 2.6^{a}$		1,2	T III	THK I	THK .
Incidental Inhalation-Powder	45. 58 ^b	35. 3b	0.015-1.4	**	2 ^b	NR	NR	2
mendentar innaration-i owder	45, 50	55,5	0.015-1.4, $0.045,25^{\circ}$		2		INK	2
Darmal Contact	1994	104	0.043-23	**	4	2	1.4.5	014
Denhar Contact	2ª	2ª	0.00023-23 ND	**	4 ND	2 ND	1-4.5 ND	0.1-4 ND
Lein Nen Celerine	104	2	0.00052.4.0	**	ND	ND		ND
Hair - Non-Coloring	184	3	0.00052-4.9	**	NK	NR	NK 0.15	NK
Hair-Coloring	1/	14	0.36-3.6	**	NK	NR	0.15	NK
Nail	436	53	0.54-98.6	**	1	NR	NR	NK
Mucous Membrane	1297	36	0.0003-4.2	**	NR	NR	2.2-2.7	4
Baby Products	14	NR	0.26-1.4	**	NR	NR	NR	NR
		Acrylates	Crosspolymer-3			Acrylates	Crosspolymer-4	
	2018 ²⁴		201820		201824		2018 ²⁰	
Totals*	4		1.6		16		3.1	
Duration of Use								
Leave-On	3		1.6		NR		3.1	
Rinse-Off	1		NR		16		NR	
Diluted for (Bath) Use	NR		NR		NR		NR	
Exposure Type								
Exposure Type	1		NR		NR		NR	
Incidental Ingestion	ND		NP		NP		NP	
Incidental Inhalation-Spray	2 ^a		1.6^{a}		NR		NR	
Incidental Inhalation Boyudar	ND		ND		ND		2.10	
Dermal Contest	ND		ND		16		J.I ND	
Decidement (undercomp)	ND		ND		10 ND			
					INK		INK	
Hair - Non-Coloring	3		1.0		NR		NR	
Hair-Coloring	NK		NK		NK		NK	
Nail	NR		NR		NR		NR	
Mucous Membrane	NR		NR		16		NR	
Baby Products	NR		NR		NR		NR	
	Acrylates	/Ammoniu	n Methacrylate Co	polymer	Acrylates	/Beheneth-2	5 Methacrylate C	opolymer
	2018 ²⁴	1998 ¹	201819	1998 ¹	2018 ²⁴		2018 ²⁰	
Totals*	26	1	0.00063-10	**	91		0.05-1.7	
Duration of Use								
Leave-On	11	1	0.002-10	**	53		0.3-1.7	
Rinse-Off	15	NR	0.00063-0.0025	**	37		0.05-1	
Diluted for (Bath) Use	NR	NR	NR	**	1		NR	
Exposure Type			1 1					
Eve Area	NR	1	NR	**	NR		NR	
Incidental Ingestion	1	NR	NR	**	NR		NR	
Incidental Inhelation Spray	1 ^a . 3 ^b	NP	ND	**	/8ª		$1.7 \cdot 0.05 \cdot 1.1^{a}$	
Incidental Inhalation Powder	4,5 3 ^b	NR	0.002°	**	40 ND		1.7, 0.95 - 1.1	
Dermal Contact	25	ND	0.002	**	24		0.2.8	
Dennar Contact	25 ND	INK	0.00003-0.005	**	54 ND		U.3-8	
Deodorant (underarm)	NK	NK	INK	**	INK		NK	
Hair - Non-Coloring	NR	NR	NK	**	46		0.05-1./	
Hair-Coloring	NR	NR	NR	**			0.2-1	
Nail	NR	NR	10	**	NR		NR	
Mucous Membrane	7	NR	0.00062	**	10		NR	
Baby Products	NR	NR	NR	**	NR		NR	

Table 4. Current and historical (where applicable) frequency and concentration of use, according to duration and exposure

	# of I	Isas	Max Conc.	of Use (%)	# of Us	as	Max Conc. or	f Use (0%)
	# 0j C	/Ses	Max Cone e	<u>y Use (70)</u>	# 05 03		Max Cone of	Use (70)
	Acrylates	/C10-30 Alk	yl Methacrylate (Copolymer	Acrylates/	C10-30AI	kyl Acrylate Cross	polymer
					('polymer	rized in sol	vents other than b	enzene)
	2018 ²⁴		2018 ²⁰		201824	2011 ² [†]	2018 ^{21 †}	2011 ² [†]
Totals*	NR		0.0001-1.1		3135	1696	0.000045-3	0.0002-5
Duration of Use								
Leave-On	NR		0.0001-1.1		2577	1365	0.000045-3	0.0002-5
Rinse-Off	NR		0.0005-0.001		546	313	0.1-1.8	0.002-5
Diluted for (Bath) Use	NR		NR		12	18	0.15	1
Exposure Type	111				12	10	0110	-
Exposure Type	ND		NP		215	132	0.12.0.0	0.003.2
Insidental Insection	ND		ND		215	152	0.12-0.9	0.005-2
Incidental Ingestion	ND		0.0001		1	70 ^a	0.0	0.3
Incidental Innalation-Spray	INK		0.0001		176; 1167 ^a ; 770 ^b	70	0.08-2; 0.11-0.2 ^a	0.03-2
Incidental Inhalation-Powder	NR		NR		77 ^b ; 4 ^c	6	0.000045-0.6; 0.07-2°	0.0002-0.1
Dermal Contact	NR		0.15-0.3		2992	1591	0.00045-3	0.0002-5
Deodorant (underarm)	NP		0.15 0.5 NP		2772 3ª	1371 1 ^a	$0.000045^{\circ}5^{\circ}$	0.0002 5
	INK		INK		5	1	0.2 (spray)	0.001
Hair - Non-Coloring	NR		0.0001-1.1		95	77	0.19-2	0.1-2
Hair-Coloring	NR		NR		35	11	0.19-1.8	0.4-5
Nail	NR		NR		8	9	0.05-1	0.1-1
Mucous Membrane	NR		NR		175	111	0.15-0.6	0.002-3
Baby Products			0.15		17	10	0.3	0.2
	Acrylates	/C12-22 Alk	yl Methacrylate (Copolymer	Acrylat	es/Ethylhe	xyl Acrylate Copo	lymer
	2018 ²⁴		2018 ²⁰		201824		2018 ²⁰	
Totals*	9		0.23-1.4		60		0.25-30	
Duration of Use	r -			i				
Leave On	0		0 23 1 4		60		0 25 30	
Pines Off	ND		0.23-1.4 ND		NP		0.25-50 ND	
Diluted for (Bath) Use	ND		ND		NR		NR	
European Trans	IVIN		IVIN		IVIA		IVA	
Exposure Type	1	1	0.00	1			0.0.20	
Eye Area	1		0.23		53		0.9-30	
Incidental Ingestion	NR		NR		NR		NR	
Incidental Inhalation-Spray	5ª; 1º		1; 0.9 ^a		NR		NR	
Incidental Inhalation-Powder	10		0.45-1.4°		NR		0.25°	
Dermal Contact	9		0.23-1.4		19		0.25-20.1	
Deodorant (underarm)	NR		NR		NR		NR	
Hair - Non-Coloring	NR		NR		NR		NR	
Hair-Coloring	NR		NR		NR		NR	
Nail	NR		NR		2		NR	
Mucous Membrane	NR		NR		NR		NR	
Baby Products	NR		NR		NR		NR	
	Acrvlat	es/Ethvlhex	vl Acrvlate Cross	polymer	Acrylates/	Hvdroxve	sters Acrvlates Co	polymer
	2018 ²⁴	2011 ²	2018 ²¹	2011 ²	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹
Totals*	3	NR	1-5.4	4-6	35	NR	0.71-6	**
Duration of Use	5		1-5.4		55	111	0.71-0	
Lagua On	2	ND	151	1.6	30	ND	0.71.6	**
Divers Off	ND	NA	1-J.4	4-0 ND	50	NA	0.71-0	**
Rinse-Off	NK ND	NK ND	NK ND	NK ND) ND	NK ND	IVK ND	**
Difuted for (Bain) Use	IVK	IVK	INK	IVK	IVK	IVK	IVK	
Exposure Type		100		-	<u>^</u>		0.0	10.11
Eye Area	NR	NR	NR	6	8	NR	0.8	**
Incidental Ingestion	1	NR	NR	NR	NR	NR	NR	**
Incidental Inhalation-Spray	NR	NR	NR	NR	15; 5 ^a ; 1 ^b	NR	0.71-6	**
Incidental Inhalation-Powder	NR	NR	1-3.1; 4.5 [°]	NR	NR	NR	NR	**
Dermal Contact	NR	NR	1-5.4	4-6	2	NR	NR	**
Deodorant (underarm)	NR	NR	NR	NR	NR	NR	NR	**
Hair - Non-Coloring	NR	NR	NR	NR	25	NR	0.71-6	**
Hair-Coloring	NR	NR	NR	NR	NR	NR	NR	**
Nail	2	NR	NR	NR	NR	NR	NR	**
Mucous Membrane	1	NR	NR	NR	NR	NR	NR	**
Baby Products	NR	NR	NR	NR	NR	NR	NR	**

Table 4. Current and historical (where app	plicable) frequency and	concentration of use, accordin	g to duration and ex	posure
--------------------------------------------	-------------------------	--------------------------------	----------------------	--------

Table 4. Current and instoric		leas	Mar Cone of	$T_{Ise}(\theta_{a})$		anon anon 1995	Max Cone of	f Use (0%)
	# Of C	Jses Inthovy PF	Max Conc of	Copolymer	# of U	ses tos/Palmath	Max Conc of	olymer
	2018 ²⁴	ICHIOXY FE	2018 ²⁰	Coporymer	2018 ²⁴	us/1 anneth	2018 ²⁰	Jiymei
Totals*	NR		0 4-1 4		9		0 53-1 3	
Duration of Use		1	7.1-1.1		,	1	0.00-1.0	
Leave-On	NR		0.4-1.4		2		NR	
Rinse-Off	NR		NR		7		0.53-1.3	
Diluted for (Bath) Use	NR		NR		NR		NR	
Exposure Type		1						
Eve Area	NR		NR		NR		NR	
Incidental Ingestion	NR		NR		NR		NR	
Incidental Inhalation-Spray	NR		1.4; 0.4 ^a		1 ^b		NR	
Incidental Inhalation-Powder	NR		NR		1 ^b		NR	
Dermal Contact	NR		NR		6		1.3	
Deodorant (underarm)	NR		NR		NR		NR	
Hair - Non-Coloring	NR		0.4-1.4		NR		NR	
Hair-Coloring	NR		NR		3		0.53	
Nail	NR		NR		NR		NR	
Mucous Membrane	NR		NR		2		NR	
Baby Products	NR		NR		NR		NR	
	Acrylate	s/Steareth-	20 Methacrvlate Co	polvmer	Acrvlates/	Steareth-20	Methacrvlate Cro	sspolymer
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	201824	2011 ²	2018 ²¹	2011 ²
Totals*	65	35	0.06-2	**	4	NR	0.37-2.3	0.1-2
Duration of Use		1	-ii					
Leave-On	22	10	0.06-0.5	**	2	NR	2.3	0.1-2
Rinse-Off	43	24	0.3-2	**	2	NR	0.37-1.6	1
Diluted for (Bath) Use	NR	1	NR	**	NR	NR	NR	NR
Exposure Type		:	-i			1	1	
Eye Area	2	NR	0.11-0.21	**	NR	NR	NR	NR
Incidental Ingestion	1	NR	NR	**	NR	NR	NR	NR
Incidental Inhalation-Spray	2; 4 ^a ; 9 ^b	2; 7 ^a	0.06-0.5	**	1 ^a ; 1 ^b	NR	2.3ª	NR
Incidental Inhalation-Powder	9 ^b	NR	0.09 ^c	**	1 ^b	NR	NR	NR
Dermal Contact	36	14	0.06-1.8	**	1	NR	1.6	0.1-1
Deodorant (underarm)	NR	NR	NR	**	NR	NR	NR	NR
Hair - Non-Coloring	19	15	0.45-0.5	**	1	NR	2.3	2
Hair-Coloring	9	5	0.54-2	**	2	NR	0.37	NR
Nail	NR	1	NR	**	NR	NR	NR	NR
Mucous Membrane	7	2	0.3	**	NR	NR	NR	1
Baby Products	1	2	NR	**	NR	NR	NR	NR
	Acrvlate	s/Steareth-	30 Methacrvlate Co	polvmer	Acrvla	tes/Stearvl I	Methacrvlate Cop	olvmer
	2018 ²⁴		2018 ²⁰	1	201824		2018 ²⁰	- J
Totals*	NR		0.03-2.1		NR		0.014-0.04	
Duration of Use								
Leave-On	NR		0.03-0.87		NR		0.014-0.04	
Rinse-Off	NR		1.8-2.1		NR		0.02-0.04	
Diluted for (Bath) Use	NR		NR		NR		NR	
Exposure Type				•		·		
Eye Area	NR		0.03		NR		NR	
Incidental Ingestion	NR		NR		NR		NR	
Incidental Inhalation-Spray	NR		0.2-0.6; 0.87 ^a		NR		0.014-0.04 ^a	
Incidental Inhalation-Powder	NR		NR		NR		NR	
Dermal Contact	NR	-	0.15-2.1		NR		0.04	
Deodorant (underarm)	NR		NR		NR		NR	
Hair - Non-Coloring	NR		0.2-0.87		NR		0.014-0.04	
Hair-Coloring	NR		NR		NR		NR	
Nail	NR		NR		NR		NR	
Mucous Membrane	NR		2.1		NR		NR	
Baby Products	NR		NR		NR		NR	

Table 4. Curi	ent and historical (when	e applicable) fr	requency and concent	tration of use, accor	ding to duration and ex	posure
---------------	--------------------------	------------------	----------------------	-----------------------	-------------------------	--------

Table 4. Current and Instorice	# of	Incable) frequ	Max Conce	of Use (%)	$\# \circ f I$	1505	Max Conc.	of Use (%)
	<i># 0</i> j	Acrylates	/VA Copolymer	-j 0.50 (70)	<i>π 0 j</i> 0	Acrylates/V	A Crossnolvmer	
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	2018 ²⁴		2018 ²⁰	
Totals*	1	NR	2,5-50	**	1		25	
Duration of Use	_			:				:
Leave-On	1	NR	2.5-50	**	1		25	
Rinse-Off	NR	NR	NR	**	NR		NR	
Diluted for (Bath) Use	NR	NR	NR	**	NR		NR	
Exposure Type		•		•				•
Eye Area	1	NR	2.5	**	NR		NR	
Incidental Ingestion	NR	NR	NR	**	NR		NR	
Incidental Inhalation-Spray	NR	NR	NR	**	NR		NR	
Incidental Inhalation-Powder	NR	NR	NR	**	NR		NR	
Dermal Contact	NR	NR	50	**	NR		NR	
Deodorant (underarm)	NR	NR	NR	**	NR		NR	
Hair - Non-Coloring	NR	NR	NR	**	NR		NR	
Hair-Coloring	NR	NR	NR	**	NR		NR	
Nail	NR	NR	NR	**	1		25	
Mucous Membrane	NR	NR	NR	**	NR		NR	
Baby Products	NR	NR	NR	**	NR		NR	
	Acryla	tes/Vinyl Iso	decanoate Cross	polymer	Acrylat	es/Vinyl Neo	decanoate Cross	polymer
	2018 ²⁴	2011 ²	2018 ²¹	2011 ²	2018 ²⁴	2011 ²	2018 ²¹	2011 ²
Totals*	30	33	0.2-0.4	0.2-0.5	14	10	NR	2
Duration of Use								
Leave-On	22	25	0.25-0.4	0.3-0.5	3	4	NR	2
Rinse-Off	8	8	0.2	0.2-0.5	5	4	NR	NR
Diluted for (Bath) Use	NR	NR	NR	NR	6	2	NR	NR
Exposure Type								
Eye Area	1	NR	NR	NR	1	NR	NR	NR
Incidental Ingestion	NR	NR	NR	NR	NR	NR	NR	NR
Incidental Inhalation-Spray	8 ^a ; 10 ^b	NR	0.34-0.4ª	0.4	2ª	NR	NR	NR
Incidental Inhalation-Powder	10 ^b	NR	0.25 ^c	NR	NR	NR	NR	NR
Dermal Contact	30	33	0.20.4	0.2-0.5	14	10	NR	2
Deodorant (underarm)	NR	NR	NR	NR	NR	NR	NR	NR
Hair - Non-Coloring	NR	NR	NR	NR	NR	NR	NR	NR
Hair-Coloring	NR	NR	NR	NR	NR	NR	NR	NR
Nail	NR	NR	NR	NR	NR	NR	NR	NR
Mucous Membrane	NR	NR	NR	NR	10	6	NR	2
Baby Products	NR	NR	NR	NR	NR	NR	NR	NR
	Acry	lic Acid/Stea	ryl Acrylate Cop	olymer	Al	lyl Methacry	lates Crosspoly	ner
	201824		201820		201824	2011 ²	201821	20112
Totals*	NR		0.1-2		31	48	0.0034-2	0.003-2
Duration of Use		1		1	27		0.0004.0	0.000.0
Leave-On	NR		0.1-2		27	44	0.0034-2	0.003-2
Rinse-Off	NR		0.25		4	4	0.075-1	0.1
Diluted for (Bath) Use	NR		NR		NR	NR	NR	NR
Exposure Type		1		1				1 .
Eye Area	NR		NR		NR	4	0.0034	4
Incidental Ingestion	NR		NR		7	16	0.034	16
Incidental Inhalation-Spray	NR		0.1; 2ª		7ª; 4º	2 ^a	1 ^a	2ª
Incidental Inhalation-Powder	NR		NR		4 ^b	2	2; 0.4-2 ^c	2
Dermal Contact	NR		NR		23	31	0.0034-2	31
Deodorant (underarm)	NR		NR		NR	NR	NR	NR
Hair - Non-Coloring	NR		0.1-2		1	NR	NR	NR
Hair-Coloring	NR		NR		NR	NR	NR	NR
Nail	NR		NR		NR	NR	NR	NR
Mucous Membrane	NR		NR		7	16	0.034	16
Baby Products	NR	1	NR NR		NR	NR	NR	NR

Table 4. Current and historical (where applicable) frequency and concentration of use, according to duration a	ad exposure
----------------------------------------------------------------------------------------------------------------	-------------

Table 4. Current and instoric	# of 1	licable) Hey	Max Conc of	Use (%)		ses	Max Conc.	of Use (%)
	A	mmonium A	Acrylates Copolyme	er	Ammoni	Ammonium Acrylates/Methyl Styrene/Styre Copolymer		
	2018 ²⁴	1998 ¹	201819	1998 ¹	2018 ²⁴		2018 ²⁰	
Totals*	60	21	0.0057-19.5	**	5		0.9	
Duration of Use		•	•		•			•
Leave-On	60	21	0.3-19.5	**	5		0.9	
Rinse-Off	NR	NR	0.0057-0.046	**	NR		NR	
Diluted for (Bath) Use	NR	NR	NR	**	NR		NR	
Exposure Type								
Eye Area	47	21	0.8-19.5	**	5		0.9	
Incidental Ingestion	NR	NR	NR	**	NR		NR	
Incidental Inhalation-Spray	1 ^b	NR	NR	**	NR		NR	
Incidental Inhalation-Powder	1 ^b	NR	NR	**	NR		NR	
Dermal Contact	20	3	0.0057-19.5	**	5		0.9	
Deodorant (underarm)	NR	NR	NR	**	NR		NR	
Hair - Non-Coloring	NR	NR	NR	**	NR		NR	
Hair-Coloring	NR	NR	NR	**	NR		NR	
Nail	10	NR	0.3-7.8	**	NR		NR	
Mucous Membrane	NR	NR	NR	**	NR		NR	
Baby Products	NR	NR	NR	**	NR		NR	
		Ammoni	um Polyacrylate		Ammo	nium Styre	ne/Acrylates Cop	olymer
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	2018 ²⁴	8^{24} 1998 ¹ 2018 ¹⁹ 199		
Totals*	15	NR	0.000001-1.8	**	2	NR	0.052-16.5	**
Duration of Use								
Leave-On	14	NR	0.00018-1.8	**	2	NR	0.052-16.5	**
Rinse-Off	1	NR	0.000001-0.0005	**	NR	NR	NR	**
Diluted for (Bath) Use	NR	NR	NR	**	NR	NR	NR	**
Exposure Type								
Eye Area	2	NR	0.0022	**	1	NR	NR	**
Incidental Ingestion	NR	NR	NR	**	NR	NR	NR	**
Incidental Inhalation-Spray	3 ^a ; 6 ^b	NR	NR	**	1 ^a	NR	NR	**
Incidental Inhalation-Powder	6 ^b	NR	0.00018 ^c	**	NR	NR	0.052	**
Dermal Contact	14	NR	0.000001-1.8	**	2	NR	0.052	**
Deodorant (underarm)	NR	NR	NR	**	NR	NR	NR	**
Hair - Non-Coloring	NR	NR	NR	**	NR	NR	NR	**
Hair-Coloring	NR	NR	NR	**	NR	NR	NR	**
Nail	1	NR	NR	**	NR	NR	16.5	**
Mucous Membrane	1	NR	NR	**	NR	NR	NR	**
Baby Products	NR	NR	NR	**	NR	NR	NR	**
		AMP-Acr	ylates Copolymer		Behenyl Meth	Behenyl Methacrylate/t-Butyl Methacrylate Copol		
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	2018 ²⁴		2018 ²⁰	
Totals*	31	NR	0.00084-8	**	5		NR	
Duration of Use								
Leave-On	28	NR	0.00084-8	**	5		NR	
Rinse-Off	3	NR	0.51	**	NR		NR	
Diluted for (Bath) Use	NR	NR	NR	**	NR		NR	
Exposure Type		·	·			-		•
Eye Area	1	NR	0.3	**	2		NR	
Incidental Ingestion	NR	NR	NR	**	3		NR	
Incidental Inhalation-Spray	12; 14 ^a	NR	0.44-8; 0.00084-1.1ª	**	NR		NR	
Incidental Inhalation-Powder	NR	NR	NR	**	NR		NR	
Dermal Contact	1	NR	0.035-0.64	**	2		NR	
Deodorant (underarm)	NR	NR	NR	**	NR		NR	
Hair - Non-Coloring	29	NR	0.00084-8	**	NR		NR	
Hair-Coloring	NR	NR	NR	**	NR		NR	
Nail	1	NR	NR	**	NR		NR	
Mucous Membrane	NR	NR	NR	**	3		NR	
Baby Products	NR	NR	NR	**	NR		NR	

1 able 4. Current and historical (where applicable) frequency and concentration of use, according to duration and exposul

Table 4. Current and instoric	# of I	leas	Max Conc. o	$f U_{Se}(\theta_{A})$	# of U		Max Conc. o	f I lso (0/2)
	# 0j C	Jses	imathaamilata C	y Use (70)	# 0J 0	ses A omulato/II-	Max Conc o	to Conclumor
	Butyl Acry	ate/Glycol 1		rossporymer	C12-22 Alkyl A	Acrylate/Hy		tte Copolymer
	2018	2011	2018	2011	2018		2018	
	1	NK	4.2-10	NK	NK		3	
Duration of Use	1	N/D	(2.10	L ND	100	1		
Leave-On		NR	4.2-10	NR	NR		3	
Rinse-Off	NR	NR	NR	NR	NR		NR	
Diluted for (Bath) Use	NR	NR	NR	NR	NR		NR	
Exposure Type								
Eye Area	NR	NR	8.3-8.5	NR	NR		NR	
Incidental Ingestion	NR	NR	NR	NR	NR		NR	
Incidental Inhalation-Spray	1ª	NR	NR	NR	NR		NR	
Incidental Inhalation-Powder	NR	NR	4.2	NR	NR		NR	
Dermal Contact	1	NR	4.2-10	NR	NR		3	
Deodorant (underarm)	NR	NR	NR	NR	NR		NR	
Hair - Non-Coloring	NR	NR	NR	NR	NR		NR	
Hair-Coloring	NR	NR	NR	NR	NR		NR	
Nail	NR	NR	NR	NR	NR		NR	
Mucous Membrane	NR	NR	NR	NR	NR		NR	
Baby Products	NR	NR	NR	NR	NR		NR	
	C8-22 Alkyl	Acrylates/M	Iethacrylic Acid (Crosspolymer		Ca	rbomer	
	2018 ²⁴	2011 ²	2018 ²¹	2011 ²	2018 ^{24 #}	2001 ^{6 ##}	2018 ²²	2001 ⁶
Totals*	2	NR	NR	NR	6434	1504	0.00001-15	0.001-2
Duration of Use		•				•		
Leave-On	2	NR	NR	NR	5336	1167	0.0012-15	0.001-2
Rinse-Off	NR	NR	NR	NR	1093	330	0.00001-2.5	0.003-2
Diluted for (Bath) Use	NR	NR	NR	NR	5	7	0.18-0.3	0.1-1
Exposure Type		÷	:		•		i	·
Eye Area	NR	NR	NR	NR	301	65	0.2-1.5	0.2-2
Incidental Ingestion	NR	NR	NR	NR	95	6	0.048-9	0.1-0.7
Incidental Inhalation-Sprav	1 ^b	NR	NR	NR	16:	50:	0.003-1:	0.3-1:
i i i i i i i i i i i i i i i i i i i					2565 ^a ; 1870 ^b	347 ^a ; 412 ^b	0.048-2.5ª	0.003-2 ^a ;
					,	ŕ		0.05-1 ^b
Incidental Inhalation-Powder	1 ^b	NR	NR	NR	2; 1870 ^b ; 30 ^c	1;	0.0012-0.88	0.3; 0.05-1 ^b ;
						412 ^b ; 5 ^c	0.1-15 ^c	0.2-0.8 ^c
Dermal Contact	1	NR	NR	NR	5601	1335	0.00001-15	0.001-2
Deodorant (underarm)	NR	NR	NR	NR	3 ^a	NR	0.25 (not spray)	NR
, , , , , , , , , , , , , , , , , , , ,					-		0.18 (spray)	
Hair - Non-Coloring	1	NR	NR	NR	490	96	0.0084-2.5	0.3-1.5
Hair-Coloring	NR	NR	NR	NR	222	57	0.2-2.5	0.7-2
Nail	NR	NR	NR	NR	12	7	0.003-0.87	0.2-2
Mucous Membrane	NR	NR	NR	NR	200	26	0.048-9	0.003-2
Baby Products	NR	NR	NR	NR	36	15	0.15-0.69	0.2-0.8
	E	thvlene/Acry	lic Acid Copolym	ier	Eth	vlene/Meth	acrylate Copolyn	ner
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹
Totals*	316	6	0.001-16.5	**	60	5	0.0003-0.83	**
Duration of Use	010	•	00001 1000		00		0100000 01000	
Leave-On	306	6	0.001-16.5	**	60	5	0.0003-0.83	**
Rinse-Off	NR	NR	0.001-0.5	**	NR	NR	NR	**
Diluted for (Bath) Use	NR	NR	NR	**	NR	NR	NR	**
Exposure Type		1. 100		1	IVIT	1.111		I
Exposure Type Eve Area	181	NR	0.001-16.5	**	20	NR	0.0003-0.74	**
Incidental Ingestion	3	NP	ND	**	NP	NP	0.3.0.59	**
Incidental Inhalation Spray	18 ^a · 7 ^b	NP	0.25	**	$2^{a} \cdot 1^{b}$	NP	0.3-0.39 NP	**
Incidental Inhalation Dowder	23.7 ^b	NP	0.20	**	0.1 ^b	NP	0 3·0 037 0 53°	**
Dermal Contact	23,7	6	0.0, 0.001-0	**	9,1	5	0.037.0.92	**
Dential Contact	290 ND		0.001-10.J	***	42 ND	J	0.037-0.83	**
Hair Non Calarina		ND		sksk	INK	INK		sk sk
Hair Calaring	I ND		INK	 **	INK		INK	**
nan-Coloring	NK	NK	INK	** **	INK	NK	INK	
INall	4	INK	4	** **	INK	INK	INK	*** **
Nucous Membrane	3	NK	NK	** 44	NR	NK	0.3-0.59	** **
Baby Products	NK	NK	NK	**	NK	NK	NK	ጥጥ

Table 4. Current and historical (where applicable) frequency and concentration of use, according to duration and	exposure
------------------------------------------------------------------------------------------------------------------	----------

	# of	Uses	Max Conc of	f Use (%)	# of L	ses	Max Conc of	Use (%)
	Eth	ylene/Sodiu	m Acrylate Copoly	mer	Ethylhexyl A	Acrylate/M	ethyl Methacrylate	Copolymer
	2018 ²⁴	1998 ¹	201819	1998 ¹	2018 ²⁴		2018 ²⁰	
Totals*	1	1	NR	**	5		7	
Duration of Use								
Leave-On	NR	1	NR	**	5		7	
Rinse-Off	1	NR	NR	**	NR		NR	
Diluted for (Bath) Use	NR	NR	NR	**	NR		NR	
Exposure Type			· · ·					
Eye Area	NR	1	NR	**	5		NR	
Incidental Ingestion	NR	NR	NR	**	NR		NR	
Incidental Inhalation-Spray	NR	NR	NR	**	NR		NR	
Incidental Inhalation-Powder	NR	NR	NR	**	NR		NR	
Dermal Contact	1	1	NR	**	5		7	
Deodorant (underarm)	NR	NR	NR	**	NR		NR	
Hair - Non-Coloring	NR	NR	NR	**	NR		NR	
Hair-Coloring	NR	NR	NR	**	NR		NR	
Nail	NR	NR	NR	**	NR		NR	
Mucous Membrane	NR	NR	NR	**	NR		NR	
Baby Products	NR	NR	NR	**	NR		NR	
		Lauryl Acr	vlate Crosspolyme	r	Lauryl	Methacryl Cr	ate/Glycol Dimetha osspolymer	crylate
	2018 ²⁴		2018 ²⁰		2018 ²⁴	2011 ²	2018 ²¹	2011 ²
Totals*	NR		1.2		99	63	1.1-3.2	0.06-3
Duration of Use								
Leave-On	NR		1.2		90	56	1.1-3.2	0.06-3
Rinse-Off	NR		NR		9	7	NR	0.2-3
Diluted for (Bath) Use	NR		NR		NR	NR	NR	NR
Exposure Type								
Eye Area	NR		NR		25	9	NR	0.1-3
Incidental Ingestion	NR		NR		19	8	1.3	0.06-2
Incidental Inhalation-Spray	NR		1.2ª		6; 2 ^b	NR	NR	0.3
Incidental Inhalation-Powder	NR		NR		6; 2 ^b	8	1.1; 3 ^c	0.01-1
Dermal Contact	NR		NR		79	53	1.1-3.2	0.06-3
Deodorant (underarm)	NR		NR		NR	1 ^a	NR	0.3ª
Hair - Non-Coloring	NR		1.2		NR	NR	NR	NR
Hair-Coloring	NR		NR		NR	NR	NR	NR
Nail	NR		NR		1	1	NR	NR
Mucous Membrane	NR		NR		19	8	1.3	0.06-2
Baby Products	NR		NR		NR	NR	NR	NR
	Laury	l Methacryl Cro	ate/Sodium Metha osspolymer	crylate	Methacry	oyl Ethyl Betaine/Acrylates Copolyme		
	2018 ²⁴	2011 ²	201821	2011 ²	2018 ²⁴	1998 ¹	201819	1998 ¹
Totals*	4	1	0.081-7.7	0.004-4	12	NR	0.00015-11	**
Duration of Use	-							
Leave-On	3	1	1.3-7.7	0.1-4	3	NR	0.09-11	**
Rinse-Off	1	NR	0.081	0.004-0.1	9	NR	0.00015-2.7	**
Diluted for (Bath) Use	NR	NR	NR	NR	NR	NR	NR	**
Exposure Type								
Eye Area	NR	NR	NR	NR	NR	NR	NR	**
Incidental Ingestion	NR	NR	NR	NR	NR	NR	NR	**
Incidental Inhalation-Sprav	NR	NR	1.3	NR	3ª	NR	0.09-3.6: 5.1-11 ^a	**
Incidental Inhalation-Powder	NR	NR	7.7°	NR	NR	NR	NR	**
Dermal Contact	4	1	0.081-7.7	0.004-4	NR	NR	NR	**
Deodorant (underarm)	NR	NR	4.6 (not spray)	NR	NR	NR	NR	**
Hair - Non-Coloring	NR	NR	NR	NR	4	NR	0.09-11	**
Hair-Coloring	NR	NR	NR	NR	8	NR	0.00015-2.7	**
Nail	NR	NR	NR	NR	NR	NR	NR	**
Mucous Membrane	1	NR	0.081	NR	NR	NR	NR	**
Baby Products	NR	NR	NR	NR	NR	NR	NR	**
Duc 1 1 June 15	1 1 1 1	: 111	1111	1111	1111	: 1111	1111	

Table 4. Curren	t and historical (where	applicable	e) frequency and c	oncentration of use,	according to duration	n and exposure
-------------------------	-------------------------	------------	--------------------	----------------------	-----------------------	----------------

Table 4. Current and historic	ai (where app	ncable) nequ	lency and concer				exposure	ATT (0.1)		
	# of	Uses	Max Conc o	of Use (%)	# of U	lses	Max Conc o	of Use (%)		
	Methyl Methacrylate Crosspolymer				Methyl Methacrylate/Glycol Dimethacrylate					
						Cro	sspolymer			
	2018 ²⁴	2008 ³	2018 ²³	2009 ³	2018 ²⁴	2008 ³	201823	2009 ³		
Totals*	423	144	0.0001-13	0.1-14	38	7	0.39-1.6	0.1-3		
Duration of Use										
Leave-On	117	142	0.0001-13	0.1-14	38	7	0.30-1.6	0.1-3		
Pinso Off		2	0.12	NP	NP	, NP	NP	0.1 5		
Diluted for (Bath) Use	ND		0.12 MD	ND		ND	ND	0.1		
Ditulea for (Bain) Use	INK	IVK	IVK	IVK	IVK	IVK	INK	IVK		
Exposure Type	50		0.10	0.5.10						
Eye Area	53	15	2-13	0.5-10	2	NR	1.4	NR		
Incidental Ingestion	38	15	2	1-10	NR	NR	NR	NR		
Incidental Inhalation-Spray	5; 46 ^a ; 39 ^b	1; 24 ^ª ; 16 [°]	0.12-0.38; 0.0069 ^a	0.1-0.6; 0.8-3 ^a ; 0.1-3 ^b	5 ^a ; 11 ^b	1 ^a	NR	0.5 ^a ; 0.2 ^b		
Incidental Inhalation-Powder	36; 39 ^b	17; 16 ^b	7.6-12; 0.5-8°	0.8-8; 0.1-3 ^b	1;11 ^b	NR	0.65; 1-1.5 ^c	3; 0.2 ^b		
Dermal Contact	370	127	0.0069-13	0.1-14	38	7	0.39-1.6	3		
Deodorant (underarm)	1 ^a	NR	2 (not spray)	0.9ª	NR	NR	NR	NR		
Hair - Non-Coloring	1	NR	NR	0.1	NR	NR	NR	NR		
Hair Coloring	7	ND	0.12	ND	ND	ND	ND	ND		
N ₁ :1	2	1	0.12	1	ND		ND			
Nall	2	1	0.0001-4	1 10	INK	INK	INK	NK		
Mucous Membrane	38	15	2	1-10	NK	NR	NK	NK		
Baby Products	NR	NR	NR	NR	NR	NR	NR	NR		
	Methyl N	lethacrylate/	PEG/PPG-4/3 M	ethacrylate		Poly C10-3	30 Alkyl Acrylate			
		Cro	sspolymer							
	2018 ²⁴		2018 ²⁰		2018 ²⁴		2018 ²⁰			
Totals*	1		NR		19		0.5-3.2			
Duration of Use			•				•	•		
Leave-On	1		NR		19		0.5-3.2			
Rinse-Off	NR		NR		NR		NR			
Diluted for (Bath) Use	NR		NR		NR		NR			
Eurogung Tung	IVIX		IVIX		IVIX		IVIN	l		
Exposure Type	ND	1	ND		2		2.0	I		
Eye Area	NK		NK	-	2		3.2			
Incidental Ingestion	NR		NR		3		0.52-1.2			
Incidental Inhalation-Spray	NR		NR		9ª; 3º		NR			
Incidental Inhalation-Powder	NR		NR		3"		2°			
Dermal Contact	1		NR		15		0.5-2			
Deodorant (underarm)	NR		NR		NR		NR			
Hair - Non-Coloring	NR		NR		NR		NR			
Hair-Coloring	NR		NR		NR		NR			
Nail	NR		NR		NR		NR			
Mucous Membrane	NR		NR		3		0.5-1.2			
Baby Products	NR		NR	-	NR		NR			
Duby Hoducis	111	Doby	and and a second		THE	Dolyoomilat	1 Crossnolumor	•		
	201924	1 Uly	2019 ²⁰		201824	1 Olyacı ylat	2019 ²⁰			
T-4-1-*	2018		2010 NG		2018		2018			
	3		END.		14		0.2-2	1		
Duration of Use	-	1	1.0	1		1	1.00	I		
Leave-On	2		NS		4		NR			
Rinse-Off	1		NS		10		0.2-2			
Diluted for (Bath) Use	NR		NS		NR		NR			
Exposure Type								<u> </u>		
Eye Area	NR		NS		NR		NR			
Incidental Ingestion	NR		NS		NR		NR			
Incidental Inhalation-Sprav	1 ^a		NS		1ª; 3 ^b		NR			
Incidental Inhalation-Powder	NR		NS		NR		NR			
Dermal Contact	NR		NS		11		0.2-2			
Doodoront (undersome)			NC		11 ND		ND			
Usin Non Coloring		-	GVI NC	-			NK			
Hair - Noil-Coloring	3		GNI		3 ND		INK			
Hair-Coloring	NR		NS		NR		NK			
Nail	NR		NS		NR		NR			
Mucous Membrane	NR		NS		6		1.5			
Baby Products	NR		NS		NR		NR			

Table 4. Current and historical (where applicable) frequency and concentration of use, according to duration and exposure

Table 4. Current and instorie		leable) freq	Man Concent	Les (0/)		ii auon anu	Man Camposul	(11 - (0/))
	# of C	ses	Max Conc of	Use (%)	# of U	ses	Max Conc o	f Use (%)
	24	Polya	acrylic Acid		24	Polyet	hylacrylate	1
	201824	1998 ¹	201819	1998'	201824		201825	
Totals*	111	31	0.0012-4	**	4		NR	
Duration of Use								
Leave-On	96	27	0.0012-4	**	4		NR	
Rinse-Off	15	7	0.0049-0.4	**	NR		NR	
Diluted for (Bath) Use	NR	NR	0.36	**	NR		NR	
Exposure Type		•	· · ·					•
Eye Area	8	NR	0.5-2.1	**	2		NR	
Incidental Ingestion	2	NR	0.0049-0.048	**	NR		NR	
Incidental Inhalation-Spray	1: 34 ^a : 29 ^b	3 ^a : 14 ^b	0.0049-0.62 ^a	**	NR		NR	
Incidental Inhalation-Powder	2.9 ^b	14 ^b	$0.0012: 0.25-4^{\circ}$	**	NR		NR	
Dermal Contact	95	28	0.0012-4	**	1		NR	
Deodorant (underarm)	NR	NR	NR	**	NR		NR	
Hair Non Coloring	2	1	0412	**	ND		ND	
Hair Coloring	ND	1 ND	0.4-1.2 ND	**	ND		ND	
N-1			NK ND	**	1			
INall	11	2	NK	**	I ND		NK ND	
Mucous Membrane	3		0.0049-0.4		INK		INK	
Baby Products	NK	NK	0.15	~~	NK	D 1	NK	
	24	Polyme	ethyl Acrylate		24	Polymethy	VI Methacrylate	
	201824		201820		201824	20083	201823	20093
Totals*	1		0.0014-5.9		922	892	0.0036-44.6	0.01-45
Duration of Use								
Leave-On	1		0.0014-5.9		896	879	0.0036-44.6	0.01-45
Rinse-Off	NR		NR		26	13	0.009-15.6	0.3-6
Diluted for (Bath) Use	NR		NR		0	NR	NR	NR
Exposure Type		•						•
Eve Area	NR		4-5.9		293	304	1-9.8	0.1-45
Incidental Ingestion	NR		2		72.	60	0.16-16.1	3-20
Incidental Inhalation-Spray	1 ^a		NR		$4 \cdot 97^{a} \cdot 88^{b}$	6:	$0.1 \cdot 4 - 14.9^{a}$	0.5-20:
incluental initiation spray	-				1, 77 , 00	74 ^a · 79 ^b	0.1, 1 11.9	0.01-15 ^a .
						,		0.3-16 ^b
Incidental Inhalation-Powder	NR		5		76: 88 ^b	93. 79p	0.27-44.6	2-30
mendental initiatation-1 owder	INK		5		70,00	,,,,,	0.27 - 44.0, $0.23 - 8.6^{\circ}$	0.3-16 ^b
Dermal Contact	1		0550		807	806	0.009.44.6	0.01.45
Deciderant (undererm)	I ND		0.5-5.9 ND		ND	ND	0.009-44.0 ND	0.01-45
Lein Nen Celerine			ININ				NK 0.1.14.0	4
Hair - Non-Coloring			INK		4	2	0.1-14.9	0.5-1
Hair-Coloring	NR		NR		9	1	15.6	2
Nail	NR		0.001444		19	14	0.0036-19	0.7-30
Mucous Membrane	NR		2		78	62	0.16-16.1	3-20
Baby Products	NR		NR		NR	NR	NR	NR
	P	otassium A	crylates Copolymer	r	Potassium Acrylates/C10-30 Alkyl Acrylate Crosspolymer			
	2018 ²⁴		2018 ²⁰		201824	2011 ²	2018 ²¹	2011 ²
Totals*	16		0.00031-1 3		2.510	NR	03	NR
Duration of Use	10	1	0.0001-1.0			1111	0.0	111
Lague-On	10		13		2	ND	ND	NP
Pinso Off	6		0.00031.0.21			ND	0.2	ND
Diluted for (Path) Use			0.00051-0.51			ND	0.3 ND	
Diffued for (Bain) Use	IVK		IVK		IVK	IVK	IVK	IVK
Exposure Type		I			T .			
Eye Area	NR		NK		1	NR	NR	NK
Incidental Ingestion	NR		NR		NR	NR	NR	NR
Incidental Inhalation Spray	NP		NP		1 ^b	ND	NP	NP
Incidental Inhalation Davidar			1 2 ^C		1 1 ^b	ND		ND
Darmal Contact	14		1.3 ND		1	ND		INK
Dermai Contact	14 ND		NK		2	INK	U.3	NK ND
Deodorant (underarm)	NK		NK		NK	NK	NK	NR
Hair - Non-Coloring	2		0.00031		NR	NR	NR	NR
Hair-Coloring	NR		NR		NR	NR	NR	NR
Nail	NR		NR		NR	NR	NR	NR
Mucous Membrane	1		NR		NR	NR	NR	NR
Baby Products	12		0.00031		NR	NR	NR	NR

Table 4. Current and historical (where applicable) frequency and concentration of use, according to duratio	n and exposure
-------------------------------------------------------------------------------------------------------------	----------------

Table 7. Current and instorie	ai (where app	11 (abic) 11 eq		and the set of the set	iccorung to ut	n anon anu t	Aposure	
	# of	Uses	Max Conc o	of Use (%)	# of U	ses	Max Conc of	Use (%)
	24	Potassi	um Carbomer		Sodium	n Acrylate/Vi	inyl Alcohol Cope	olymer
	201824		201820		201824	_	201820	
Totals*	73		NR		NR		1.5	
Duration of Use			1					
Leave-On	56		NR		NR		NR	
Rinse-Off	13		NR		NR		1.5	
Diluted for (Bath) Use	4		NR		NR		NR	
Exposure Type								
Eye Area	3		NR		NR		NR	
Incidental Ingestion	NR		NR		NR		NR	
Incidental Inhalation-Spray	25 ^a ; 27 ^b		NR		NR		NR	
Incidental Inhalation-Powder	27 ^b		NR		NR		NR	
Dermal Contact	73		NR		NR		NR	
Deodorant (underarm)	NR		NR		NR	1	NR	
Hair - Non-Coloring	NR		NR		NR		1.5	
Hair-Coloring	NR		NR		NR	1	NR	
Nail	NR		NR		NR		NR	
Mucous Membrane	6		NR		NR		NR	
Baby Products	NR		NR		NR	-	NR	
Duby Hoduba	1,11	Sodium Aci	rvlates Copolyme	r	So	dium Acryla	tes Crosspolymer	-2
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	201824	20112	2018 ²¹	- 2011 ²
Totals*	179	5	0.005-18	**	NR	NR	0 47-1 8	0.8
Duration of Use	1//	0	0.002-10				0.47-1.0	0.0
Lagya-On	170	NR	0.005-18	**	NR	NR	0.47-1.8	0.8
Pinso Off	0	5	NP	**	NP	NR	NP	NP
Diluted for (Bath) Use	9 ND	ND	NR	**	ND	ND	ND	NP
Erma source True a	IVIA	IVA	IVA		IVI		IVI	IVIA
Exposure Type	20	ND	1.5	**	ND	ND	ND	ND
Eye Area	20	INK	1.5 ND	**	INK	NK	NK	NK
Incidental Ingestion		INK	INK	**	NK	NK	NK	NR
Incidental Inhalation-Spray	72°; 50°	NR	8°	**	NR	NR	NR	NR
Incidental Inhalation-Powder	50°; 2°	NR	0.5-1.2	**	NR	NR	0.47-1.8	NR
Dermal Contact	176	NR	0.005-18	**	NR	NR	0.47-1.8	0.8
Deodorant (underarm)	NR	NR	NR	**	NR	NR	NR	NR
Hair - Non-Coloring	1	NR	NR	**	NR	NR	NR	NR
Hair-Coloring	NR	5	NR	**	NR	NR	NR	NR
Nail	NR	NR	NR	**	NR	NR	NR	NR
Mucous Membrane	2	NR	NR	**	NR	NR	NR	NR
Baby Products	2	NR	NR	**	NR	NR	NR	NR
	Sodium Acr	ylates/C10-3	0 Alkyl Acrylate	Crosspolymer	Sodium Acr	ylates/Vinyl	Isodecanoate Cro	osspolymer
	2018 ²⁴	2011 ²	2018 ²¹	2011 ²	2018 ²⁴	2011²	2018 ²¹	2011²
Totals*	96	6	0.3	NR	NR	NR	0.55	NR
Duration of Use								
Leave-On	18	6	NR	NR	NR	NR	0.55	NR
Rinse-Off	78	NR	0.3	NR	NR	NR	NR	NR
Diluted for (Bath) Use	NR	NR	NR	NR	NR	NR	NR	NR
Exposure Type			•				·	
Eye Area	2	NR	NR	NR	NR	NR	NR	NR
Incidental Ingestion	NR	NR	NR	NR	NR	NR	NR	NR
Incidental Inhalation-Spray	5 ^a ; 5 ^b	1	NR	NR	NR	NR	NR	NR
Incidental Inhalation-Powder	5 ^b	NR	NR	NR	NR	NR	NR	NR
Dermal Contact	96	6	0.3	NR	NR	NR	0.55	NR
Deodorant (underarm)	NR	NR	NR	NR	NR	NR	NR	NR
Hair - Non-Coloring	NR	NR	NR	NR	NR	NR	NR	NR
Hair-Coloring	ND	ND	ND	NP	NP	NP	NP	ND
Nail	ND	ND	ND	NP	ND	NP	NP	ND
Mucous Membrana	ND	ND	ND	ND	ND	ND	NP	ND
Deby Products	NK	INK	INK	INK	NR	INK		ND
DADV PTOQUCIS	I INK	INK INK	INK INK	I INK	INK		INK	INK

Table 4. Current and historical (where applicable) frequency and concentration of use, according to duration and	exposure
------------------------------------------------------------------------------------------------------------------	----------

	# of U	Jses	Max Conc o	of Use (%)	# of Us	es	Max Conc of	Use (%)
		Sodiu	m Carbomer			Sodiun	n Polyacrylate	
	2018 ²⁴		201822		2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹
Totals*	168		0.015-0.65		900	8	0.0001-29.7	**
Duration of Use				•				
Leave-On	146		0.015-0.65		782	5	0.0001-29.7	**
Rinse-Off	22		NR		118	3	0.0002-1.5	**
Diluted for (Bath) Use	NR		0.16		NR	NR	NR	**
Exposure Type								
Eye Area	22		0.015		131	NR	0.9-29.7	**
Incidental Ingestion	NR		NR		3	NR	0.0095-0.09	**
Incidental Inhalation-Spray	76 ^a ; 39 ^b		0.65 ^a		1; 319 ^a ; 267 ^b	1	0.0001-1.8 0.0005-0.0098 ^a ;	**
Incidental Inhalation-Powder	39 ^b		0.028-0.13 ^c		7; 267 ^b	NR	0.05; 1.5 ^b · 0.0015-7 ^c	**
Dermal Contact	166		0.015-0.16		774	5	0.0005-7	**
Deodorant (underarm)	NR		NR		NR	NR	1.5 (not spray) 2.9 (spray)	**
Hair - Non-Coloring	NR		0.65		83	NR	0.0001-1.8	**
Hair-Coloring	NR		NR		22	3	1.5	**
Nail	1		NR		1	NR	6	**
Mucous Membrane	1		0.16		16	2	0.0098-0.8	**
Baby Products	NR		NR		NR	- NR	0.55	**
		Sodium P	olymethacrylate	1	Steareth	-10 Allvl F	ther/Acrylates Conc	olymer
	201824	Sourann	2018 ²⁰		2018 ²⁴	10741911	2018 ¹⁹	1008 ¹
Totals*	67		0.063-3.4		67	6	0.025-1.5	**
Duration of Use	02	1	0.003-3.4	1	02	U	0.040-1.0	
	62		0.062.2.4	1	51	ND	0.025.1.5	**
Leave-On	02		0.005-5.4			INK 6	0.025-1.5	4-4- 4-4
Rinse-Ojj							1.J ND	4 4 4 4
Diluted for (Bain) Use	IVK		IVK		INK	IVK	IVK	4.4
Exposure Type	(0)	1	0.0(2.1.5	1	ND	ND	ND	**
Eye Area	60		0.063-1.5		NK	NK	NK	**
Incidental Ingestion	NK		NK		NK	NR	NK	**
Incidental Inhalation-Spray	l"		NR		53"; 1"	NR	0.025-1.5"	**
Incidental Inhalation-Powder	NR		NR		10	NR	NR	**
Dermal Contact	8		0.5-1.5		3	NR	NR	**
Deodorant (underarm)	NR		NR		NR	NR	NR	**
Hair - Non-Coloring	NR		3.4		53	NR	0.025-1.5	**
Hair-Coloring	NR		NR		6	6	NR	**
Nail	NR		NR		NR	NR	NR	**
Mucous Membrane	NR		NR		1	NR	NR	**
Baby Products	NR		NR		NR	NR	NR	**
	Styrene/Acry	lates/Ammo	onium Methacryla	te Copolymer	VA/Butyl N	laleate/Iso	obornyl Acrylate C	opolymer
	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹	2018 ²⁴	1998 ¹	2018 ¹⁹	1998 ¹
Totals*	106	1	1.2-38	**	2	5	1.3-10	**
Duration of Use								
Leave-On	102	1	1.2-38	**	2	5	1.3-10	**
Rinse-Off	4	NR	10	**	NR	NR	NR	**
Diluted for (Bath) Use	NR	NR	NR	**	NR	NR	NR	**
Exposure Type				1				
Eve Area	99	1	1.2-22.6	**	NR	NR	NR	**
Incidental Ingestion	NR	NR	NR	**	NR	NR	NR	**
Incidental Inhalation-Spray	1 ^a	NR	NR	**	1 · 1 ^a	NR	1.3-10	**
Incidental Inhalation-Dowder	NR	NR	NR	**	NR	NR	NR	**
Dermal Contact	50	1	33076	**	ND	ND	13.2	**
Decidement (underserve)	50 ND		3.3-22.0	**			1.3-2 ND	**
Leodorant (underarm)	INK	NK	NK	4 T	NK	NK -		**
Hair - Non-Coloring	NR	NK	NR	**	2	5	2.5-10	**
Hair-Coloring	4	NR	10	**	NR	NR	NR	**
Nail	1	NR	21-38	**	NR	NR	NR	**
Mucous Membrane	NR	NR	NR	**	NR	NR	NR	**
Baby Products	NR	NR	NR	**	NR	NR	NR	**

*Because each ingredient may be used in cosmetics with multiple exposure types, the sum of all exposure types may not equal the sum of total uses

** Concentration of use data were not provided at the time of the review.

[#] This ingredient is listed in the VCRP as Carbomer (6175 used under the INCI name) and several tradenames (259 used listed under the tradenames)

At the time of the original assessment, this ingredient was reported under several names. The use frequencies of use were combined for the purposes of

this table; this may overestimate the actual 2001 frequency of use

^a It is possible these products are sprays, but it is not specified whether the reported uses are sprays.

^b Not specified whether a spray or a powder, but it is possible the use can be as a spray or a powder, therefore the information is captured in both categories. ^c It is possible these products are powders, but it is not specified whether the reported uses are powders

NR - no reported use

NS - not yet surveyed

Table 5. Acrylates copolymers not reported to be used in cosmetics, according to 2018 FDA VCRP²⁴ and 2018 Council survey¹⁹⁻²³ data

Acrylates/Beheneth-25 Methacrylate/Steareth-30 Methacrylate Copolymer Ethylene/Acrylic Acid/VA Copolymer	
Acrylates/C12-13 Alkyl Methacrylates/Methoxyethyl Acrylate Ethylene/Calcium Acrylate Copolymer	
Crosspolymer Ethylene/Magnesium Acrylate Copolymer	
Acrylates/C26-28 Olefin Copolymer Ethylene/Zinc Acrylate Copolymer	
Acrylates/C5-8 Alkyl Acrylate Copolymer Ethylhexyl Acrylate/Methoxy PEG-23 Methacrylate/Vi	inyl Acetate
Acrylates/Ceteareth-20 Methacrylate Crosspolymer Copolymer	
Acrylates/Ceteareth-20 Methacrylate Crosspolymer-2 Glycol Dimethacrylate Crosspolymer*	
Acrylates/Ceteth-20 Methacrylate Copolymer Glycol Dimethacrylate/Vinyl Alcohol Crosspolymer	
Acrylates/Ethylhexyl Acrylate/Glycidyl Methacrylate Crosspolymer Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copoly	mer
Acrylates/Hydroxyethyl Acrylate/Lauryl Acrylate Copolymer Lauryl Acrylate/VA Copolymer	
Acrylates/Hydroxyethyl Acrylate/Methoxyethyl Acrylate Copolymer Lauryl Acrylate/VA Crosspolymer	
Acrylates/Laureth-25 Methacrylate Copolymer Methacrylic Acid/PEG-6 Methacrylate/PEG-6 Dimetha	acrylate Crosspolymer
Acrylates/Lauryl Methacrylate Copolymer PEG/PPG-5/2 Methacrylate/Methacrylic Acid Crosspol	lymer
Acrylates/Lauryl Methacrylate/Tridecyl Methacrylate Crosspolymer Poly(Methoxy PEG-9 Methacrylate)	
Acrylates/Methoxy PEG-4 Methacrylate Copolymer Polyacrylate-29*	
Acrylates/Methoxy PEG-15 Methacrylate Copolymer Polyacrylate-34*	
Acrylates/Methoxy PEG-90 Methacrylate Crosspolymer Polybutyl Acrylate	
Acrylates/PEG-4 Dimethacrylate Crosspolymer Polybutyl Methacrylate	
Acrylates/Steareth-50 Acrylate Copolymer Polyhydroxyethylmethacrylate	
Acrylic Acid/C12-22 Alkyl Acrylate Copolymer Polyisobutyl Methacrylate	
Allyl Methacrylate/Glycol Dimethacrylate Crosspolymer Polypropyl Methacrylate	
Ammonium Acrylates/Ethylhexyl Acrylate Copolymer Polystearyl Methacrylate	
Ammonium Styrene/Acrylates/Ethylhexyl Acrylate/Lauryl Acrylate Potassium Acrylate Crosspolymer	
Copolymer Potassium Acrylates/Ethylhexyl Acrylate Copolymer	
Ammonium VA/Acrylates Copolymer Potassium Aluminum Polyacrylate	
Butyl Acrylate/Cyclohexyl Methacrylate Copolymer Potassium Polyacrylate	
Butyl Acrylate/Ethylhexyl Methacrylate Copolymer Sodium Acrylate/Acrolein Copolymer	
Butyl Acrylate/Hydroxyethyl Methacrylate Copolymer Sodium Acrylates/Beheneth-25 Methacrylate Crosspoly	ymer
Butyl Methacrylate/Acryoyloxy PG Methacrylate Copolymer Sodium Acrylates/Ethylhexyl Acrylate Copolymer	
C8-22 Alkyl Acrylates/Methacrylic Acid Crosspolymer Stearyl/Lauryl Methacrylate Crosspolymer	
Calcium Potassium Carbomer	

*not yet surveyed by the Council

Table 6. Acute toxicity studies

Ingredient	Animals	No./Group	Vehicle	Concentration/Dose/Protocol	LD ₅₀ /LC ₅₀ /Results	Reference
				DERMAL		
Acrylates/Beheneth-25 Methacrylate Copolymer	rats	not stated	not stated	details not provided	> 5 g/kg	10
Acrylates Copolymer [as 2- propenoic acid, 2-methyl-, polymer with butyl 2-methyl-2- propenoate, ethyl 2-methyl-2- propenoate and ethyl 2- propenoate]	rats	not stated	not stated	in accord with OECD TG 423; details not provided	> 2 g/kg	13
Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%)	rats	not stated	not stated	in accord with OECD TG 402; details were not provided	>5 g/kg bw	14
VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol	NZW rabbits	3/sex	applied neat	occlusive patch of 2 g/kg of the test material was applied to intact and abraded skin for 24 h	> 2 g/kg	8
				ORAL		
Acrylates/Beheneth-25 Methacrylate Copolymer	rats	not stated	not stated	details not provided	> 5 g/kg	10
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	rats (strain not specified)	5/sex	copolymer dispersion was mixed with powdered diet	the copolymer dispersion was mixed with powdered diet to give a content of 20% of dry polymer substance; animals were given the treated feed for 24 h, and then observed for 4 wks	> 25.2 g dry copolymer/kg bw no mortality; no lesions observed at necropsy	15
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	dogs (strain not specified)	2/sex	copolymer dispersion was mixed with powdered diet	the copolymer dispersion was mixed with powdered diet to give a content of 20% of dry polymer substance; fasted animals were fed 60 g formulated diet/kg bw, and then observed for clinical signs	> 7.95 g dry copolymer/kg bw no mortality; no lesions observed at necropsy	15
Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%)	rats	not stated	not stated	in accord with OECD TG 425; details not provided	> 5 g/kg	14
Polyacrylate-1 Crosspolymer	rats	not stated	DMSO	in accord with OECD TG 423; details not provided	> 2 g/kg	12
VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol	Sprague-Dawley rats	5/sex	corn oil	5 g/kg by gavage	> 5 g/kg no mortality	8
				INHALATION		
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	Wistar rats	5/sex	the copolymer was dispersed with dry matter	single 4-h exposure (nose-only) to an aerosol of the copolymer dispersion with a dry matter content of 30.2%; the test was performed in accord with OECD TG 403	> 3960 mg/l no mortality; no observations of toxicity	15

Abbreviations: DMSO - dimethyl sulfoxide; NZW - New Zealand White; OECD - Organisation for Economic Co-operation and Development; TG - test guideline

Table 7. Genotoxicity Studies

Test Article	Concentration/Dose	Vehicle	Test System	Procedure	Results	Reference
			IN VIT	RO		
Acrylates Copolymer [as 2- propenoic acid, 2-methyl-, polymer with butyl 2-methyl- 2-propenoate, ethyl 2-methyl- 2-propenoate and ethyl 2- propenoate]	not provided	not provided	not provided	Ames test, in accord with OECD TG 471; details not provided	not mutagenic	13
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	312.5 – 5000 μg dry copolymer/plate	acetone	S. typhimurium TA98, TA100, and TA1537	Ames test, with and without metabolic activation	not mutagenic	13
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	40% dry substance 3 – 5000 µg dispersion/ plate (corresponds to 1.2 – 2000 µg dry copolymer/ plate	aq. dispersion	S. typhimurium TA98, TA100, TA102, TA1535, and TA1537	Ames test in accord with OECD TG 471, with and without metabolic activation	not mutagenic	15
Acrylates Copolymer (as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid)	157 – 5000 μg dry copolymer/plate	DMSO	S. typhimurium TA98, TA100, TA1535, and TA1537; <i>E. coli</i> WP2uvrA	Ames test in accord with OECD TG 471 and 472, with and without metabolic activation	not mutagenic	16
Acrylates Copolymer [as 2- propenoic acid, 2-methyl-, polymer with butyl 2-methyl- 2-propenoate, ethyl 2-methyl- 2-propenoate and ethyl 2- propenoate]	not provided	not provided	not provided	mouse lymphoma cell assay; in accord with OECD TG 476; details not provided	not mutagenic	13
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	195.3 – 6250 µg dry copolymer /ml	deionized water	mammalian L5178Y cells	mouse lymphoma L5178Y cell mutation assay in accord with OECD TG 476; cells were exposed to the test material for 4 h in the presence and absence of metabolic activation, or for 24 h without metabolic activation	not genotoxic	15
Acrylates Copolymer (as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid)	14.5 - 5000 µg dry copolymer/ml	DMSO	mammalian L5178Y cells	mouse lymphoma L5178Y cell mutation assay in accord with OECD TG 476; cells were exposed to the test material for 4 h in the presence and absence of metabolic activation, or for 24 h without metabolic activation	not genotoxic	16
Acrylates Copolymer (as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid)	\leq 1080 µg dry copolymer/ml (Exp. 1) \leq 9000 µg dry copolymer/ml (Exp. 2)	DMSO	human lymphocytes	chromosomal aberration assay in accord with OECD TG 473 Exp 1: cells were exposed for 2 h with, and 3 h without, metabolic activation Exp. 2: cells were exposed for 24 h, with and without metabolic activation	not clastogenic	16
Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%)	not provided	not provided	not provided	Ames test, in accord with OECD TG 471; details not provided	not mutagenic	14

Table 7. Genotoxicity Studies

Test Article	Concentration/Dose	Vehicle	Test System	Procedure	Results	Reference
				IN VIVO		
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	500, 1000, and 2000 mg dry copolymer/kg bw	sterile water	mice, 5/sex/group	mouse micronucleus test in accord with OECD TG 474; mice were dosed by gavage (10 ml/kg bw) and killed 24 h after dosing; a second high- dose group was killed 48 h after dosing	not genotoxic a minimal increase of MNPCE in male mice killed after 24 h was considered not biologically relevant, and was within historical range	15
Acrylates Copolymer (as a fully polymerized copolymer of methyl acrylate, methyl methacrylate, and methacrylic acid)	500, 1000, and 2000 mg dry copolymer/kg bw	1% aq CMC	mice, 5/sex/group	mouse micronucleus test in accord with OECD TG 474; mice were dosed by gavage (10 ml/kg bw) and killed 24 h after dosing; a second high- dose group was killed 48 h after dosing	not genotoxic	16

Abbreviations: CMC - carboxymethylcellulose; DMSO - dimethyl sulfoxide; MNPCE - micronucleated polychromatic erythrocytes; OECD - Organisation for Economic Co-operation and Development; TG - test guideline

Table 8. Dermal irritation and sensitization

Test Article	Dose/Concentration	Test Population	Procedure	Results	Reference
			ANIMAL		
Acrylates/Beheneth-25 Methacrylate Copolymer	not stated	rabbits; # not stated	details not provided	classified as slightly irritating very slight to well-defined erythema and very slight edema were observed; erythema was resolved by day 7 and edema within 48 h	10
Acrylates Copolymer [as 2- propenoic acid, 2-methyl-, polymer with butyl 2-methyl-2- propenoate, ethyl 2-methyl-2- propenoate and ethyl 2- propenoate]	not stated	rabbits; # not stated	skin irritation test conducted in accord with OECD TG404; details not provided	not irritating	13
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	0.5 ml	3 NZW rabbits	4-h semi-occlusive patch was applied to each animal, in accord with OECD TG 404; test sites were observed 1, 24, 48, and 72 h after patch removal	not an irritant	15
Acrylates Copolymer [as 2- propenoic acid, 2-methyl-, polymer with butyl 2-methyl-2- propenoate, ethyl 2-methyl-2- propenoate and ethyl 2- propenoate]	not stated	not stated; assumed to be mice	LLNA, in accord with OECD TG 429	not a sensitizer	13
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	not stated; assumed neat	Dunkin-Hartley albino guinea pigs; 20 test and 10 control animals	Buehler test, performed in accord with OECD TG 406 <u>induction</u> : 6-h occlusive patches were applied 1 x/wk for 3 wks <u>challenge</u> : after a 2-wk non-treatment period, a 6-h occlusive patch was applied to an untreated site	not a sensitizer	15
Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%)	not stated	rabbits; # not stated	skin irritation test conducted in accord with OECD TG404; details not provided	slightly irritating slight erythema observed at 1 and 24 h after patch removal; skin appeared normal after 48 h	14

Table 8. Dermal irritation and sensitization

Test Article	Dose/Concentration	Test Population	Procedure	Results	Reference
VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol	0.5 g	6 NZW rabbits	24 h occlusive patch of the test material moistened with 0.5 ml physiological saline applied to intact and abraded dorsal skin	not an irritant	8
VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol	Neat; 0.5 g	10 Hartley guinea pigs	Buehler test <u>induction</u> : 6-h occlusive patch applied 3x/wk for 3 wks <u>challenge</u> : after a 2-wk non-treatment period, patches were applied to the original test site, and to a previously untested site	not an irritant or a sensitizer	8
			HUMAN		
Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%)	not provided	# subjects not provided	HRIPT; details not provided	not a sensitizer	14
VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol	5 g; slurry in alcohol	25 subjects	48-h patch test	slight erythema observed in 20% of the subjects	8
VA/Butyl Maleate/Isobornyl Acrylate Copolymer	0.2 ml in 10% ethanol	109 subjects	HRIPT induction: 24-h patches 3x/wk for 3 wks <u>challenge</u> : after a 2-wk, non-treatment period, a 24-h patch was applied to a previously untreated site	not likely to be a sensitizer <u>induction</u> : minimal erythema in 3 subjects and hyperpigmentation in 1 subject; in 1 subject, edema and intense erythema with application 8 that did not recur when the patch was moved <u>challenge</u> : minimal erythema in the subject that had a reaction with the 8 th induction patch; minimal erythema in 3 subjects that did not react during induction	8

Abbreviations: HRIPT - human repeated insult patch test; NZW - New Zealand White; OECD - Organisation for Economic Co-operation and Development; TG - test guideline

Table 9. Ocular irritation studies

Test Article	Concentration/Dose	Test Population	Procedure	Results	Reference
			ANIMAL		
Acrylates/Beheneth-25 Methacrylate Copolymer	not stated	rabbits; # not stated	details not provided	classified as slightly irritating transient conjunctival effects were observed; eyes were normal within 48 h	10
Acrylates Copolymer [as 2- propenoic acid, 2-methyl-, polymer with butyl 2-methyl-2- propenoate, ethyl 2-methyl-2- propenoate and ethyl 2- propenoate]	not stated	NZW rabbits; # not stated	in accord with OECD TG 405; details not provided	slightly irritating	13
Acrylates Copolymer (as a fully polymerized copolymer of methyl methacrylate and ethyl acrylate)	undiluted	3 NZW rabbits	0.1 ml was instilled into the conjunctival sac of one eye of each rabbits, in accord with OECD TG 405; test eyes were observed 1, 24, 48, and 72 h after patch removal	not an ocular irritant	15
Acrylates/Hydroxyesters Acrylates Copolymer (product containing < 50%)	not stated	rabbits; # not stated	details not provided	slightly irritating slight conjunctival irritation in treated eyes 1- and 24-h after instillation; irritation resolved within 48 h	14
VA/Butyl Maleate/Isobornyl Acrylate Copolymer in ethanol	undiluted	9 NZW rabbits	0.1 g was instilled into the conjunctival sac of one eye of each rabbits; the contralateral eye served as an untreated control. Following instillation, the eyes of 3 rabbits were immediately rinsed; the eyes of the remaining 6 rabbits were not rinsed.	moderate to severe eye irritant Slight corneal opacity, slight to moderate conjunctival redness, slight-to-severe conjunctival chemosis and slight to severe conjunctival discharge observed in the unwashed eyes; some degree of conjunctivitis observed in all unwashed eyes on day 7; within the first 3 days post-exposure, blistering of the conjunctiva was observed in 5 eyes that were not rinsed.	8

Abbreviations: NZW - New Zealand White; OECD - Organisation for Economic Co-operation and Development; TG - test guideline

REFERENCES

- Andersen FA (ed). Final report on the Safety Assessment of Acrylates Copolymer and 33 Related Cosmetic Ingredients. Int J Toxicol. 2002;21(Suppl 3):1-50.
- Fiume MM, Heldreth B, Boyer I, et al. Safety Assessment of Cross-Linked Alkyl Acrylates as Used in Cosmetics. Int J Toxicol. 2017;36(Suppl 2):59S-88S.
- Becker LC, Bergfeld WF, Belsito DV, et al. Final report of the Cosmetic Ingredient Review Expert Panel Safety Assessment of Polymethyl Methacrylate (PMMA), Methyl Methacrylate Crosspolymer, and Methyl Methacrylate/Glycol Dimethacrylate Crosspolymer. *Int J Toxicol.* 2011;30(Suppl 1):54S-65S.
- 4. Elder RL (ed). Final report on the safety assessment of Carbomers-934, -910, -934P, -940, -941, and -962. *J Am Coll Toxicol*. 1982;1(2):109-141.
- Nikitakis J and Kowcz A. wINCI: International Cosmetic Ingredient Dictionary and Handbook. <u>http://webdictionary.personalcarecouncil.org/jsp/Home.jsp</u>. Washington, DC. Last Updated 2018. Date Accessed 1-16-2018.
- Andersen FA (ed). Annual Review of Cosmetic Ingredient Safety Assessments 2001/2002. Int J Toxicol. 2003;22(Suppl 1):6-11.
- Johnson WJ, Heldreth B, Bergfeld WF, et al. Safety assessment of Styrene and Vinyl-type Styrene Copolymers as Used in Cosmetics. 2014. Available from CIR: https://www.cir-safety.org/ingredients.
- National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Copolymer of vinyl acetate, butyl maleate and isobornyl acrylate in ethanol. File No: NA/63. <u>https://www.nicnas.gov.au/search?query=+Copolymer+of+Vinyl+Acetate%2C+Butyl+Maleate+and+Isoborneyl+Acryl</u> <u>ate+in+Ethanol&collection=nicnas-meta</u>. Last Updated 1992. Date Accessed 1-17-2018.
- 9. National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Polymer in Allianz OPT (Acrylates/C12-22 Alkyl Methacrylate Copolymer). File No. PLC/341. <u>https://www.nicnas.gov.au/__data/assets/pdf_file/0004/9733/PLC341FR.pdf</u>. Last Updated 2003. Date Accessed 1-17-2018.
- National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Polymer in Aculyn 28 (Acrylates/Beheneth-25 Methacrylate Copolymer). File No PLC/456. <u>https://www.nicnas.gov.au/__data/assets/pdf_file/0015/10662/PLC456FR.pdf</u>. Last Updated 2004. Date Accessed 1-16-0018.
- National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Acrylates/Palmeth-25 Acrylate Co-polymer. File No: PLC/398. <u>https://www.nicnas.gov.au/__data/assets/pdf_file/0006/9780/PLC398FR.pdf</u>. Last Updated 2-24-2004. Date Accessed 1-17-2018.
- National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Carbopol Aqua CC (Polyacrylate-1 Crosspolymer). File No: LTD/1364. <u>http://webarchive.nla.gov.au/gov/20080724224929/http://nicnas.gov.au/PUBLICATIONS/CAR/NEW/LTD/LTDSUM</u> <u>MR/LTD1000SR/ltd1364.asp</u>. Last Updated 2008. Date Accessed 1-17-2018.
- National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Tilamar Fix A1000 (Acrylates Copolymer). File No. PLC/1015. <u>https://www.nicnas.gov.au/search?query=PLC%2F1015&collection=nicnas-meta</u>. Last Updated 2012. Date Accessed 1-16-0018.
- National Industrial Chemicals Notification and Assessment Scheme (NICNAS). Polymer in Acudyne DHR (Acrylates/Hydroxyesters Acrylates Copolymer). PLC/1002. <u>https://www.nicnas.gov.au/search?query=Polymer+in+Acudyne+DHR&collection=nicnas-meta</u>. Last Updated 2012. Date Accessed 1-16-0018.
- 15. Eisele J, Haynes G, Kreuzer K, et al. Characterisation and toxicological assessment of Neutral Methacrylate Copolymer for GRAS evaluation. *Regul.Toxicol Pharmacol.* 2013;67(3):392-408.

- Eisele J, Haynes G, Kreuzer K, et al. Toxicological assessment of Anionic Methacrylate Copolymer: I. Characterization, bioavailability and genotoxicity. *Regul.Toxicol Pharmacol.* 2016;82:39-47. doi: 10.1016/j.yrtph.2016.11.009. Epub;%2016 Nov 4.:39-47.
- European Food Safety Authority (EFSA). Scientific Opinion on the safety of neutral methacrylate copolymer of the proposed uses as a food additive. *EFSA Journal*. 2010;8(7):1655 <u>https://efsa.onlinelibrary.wiley.com/doi/epdf/10.2903/j.efsa.2010.1655</u>.
- 18. Dow Chemical Company. Safety Data Sheet: ACULYN[™] 22 (Acrylates/Steareth-20 Methacrylate Copolymer). <u>https://www.dow.com/en-us/elibrary#q=00183168</u>. Last Updated 9-18-2015. Date Accessed 1-19-2018.
- Personal Care Products Council. 4-5-2018. Concentration of Use by FDA Product Category: Acrylates Copolymers original report. Unpublished data submitted by Personal Care Products Council submitted on April 5, 2018.
- 20. Personal Care Products Council. 4-5-2018. Concentration of Use by FDA Product Category: Acrylates Copolymers additions. Unpublished data submitted by Personal Care Products Council.
- 21. Personal Care Products Council. 5-21-2018. Updated concentration of Use by FDA Product Category: Acrylates Crosspolymers. Unpublished data submitted by Personal Care Products Council submitted June 20, 2018.
- 22. Personal Care Products Council. 5-21-2018. Updated concentration of use by FDA Product Category: Carbomers. Unpublished data submitted by Personal Care Products Council submitted June 20, 2018.
- Personal Care Products Council. 5-21-2018. Updated concentration of Use by FDA Product Category: Polymethyl Methacrylate, Methyl Methacrylate Crosspolymer and Methyl Methacrylate/Glycol Dimethacrylate Crosspolymer. Unpublished data submitted by Personal Care Products Council submitted June 20, 2018.
- US Food and Drug Administration (FDA) Center for Food Safety & Applied Nutrition (CFSAN). Voluntary Cosmetic Registration Program (VCRP) - Frequency of Use of Cosmetic Ingredients. College Park, MD: 2018. Obtained under the Freedom of Information Act from CFSAN; requested as "Frequency of Use Data" January 3 2018; received February 5 2018).
- 25. Johnsen MA. The influence of particle size. Spray Technol Marketing. 2004;14(11):24-27.
- Rothe H. Special Aspects of Cosmetic Spray Evalulation. 9-26-2011. Unpublished data presented at the 26 September CIR Expert Panel meeting. Washington, D.C.
- Rothe H, Fautz R, Gerber E, et al. Special aspects of cosmetic spray safety evaluations: Principles on inhalation risk assessment. *Toxicol Lett.* 2011;205(2):97-104.
- Bremmer HJ, Prud'homme de Lodder LCH, and Engelen JGM. Cosmetics Fact Sheet: To assess the risks for the consumer; Updated version for ConsExpo 4. Bilthoven, Netherlands: Netherlands National Institute for Public Health and the Environment. 2006. <u>http://www.rivm.nl/bibliotheek/rapporten/320104001.pdf</u>. Date Accessed 8-24-2011. Report No. RIVM 320104001/2006. pp. 1-77.
- 29. CIR Science and Support Committee of the Personal Care Products Council (CIR SSC). 2015. (Nov 3rd) Cosmetic Powder Exposure. Unpublished data submitted by the Personal Care Products Council.
- Aylott RI, Byrne GA, Middleton J, et al. Normal use levels of respirable cosmetic talc: preliminary study. Int J Cosmet Sci. 1979;1(3):177-186. PM:19467066.
- 31. Russell RS, Merz RD, Sherman WT, et al. The determination of respirable particles in talcum powder. *Food Cosmet Toxicol*. 1979;17(2):117-122. PM:478394.
- European Commission. CosIng database; following Cosmetic Regulation No. 1223/2009. <u>http://ec.europa.eu/growth/tools-databases/cosing/</u>. Last Updated 2016. Date Accessed 4-7-2016.
- 33. Dow Chemical Company. Technical Data Sheet: Acudyne™ DHR (Acrylates/Hydroxyesters Acrylates Copolymer). <u>https://www.dow.com/assets/attachments/business/pcare/acudyne/acudyne_dhr/tds/acudyne_dhr.pdf</u>. Last Updated 2006. Date Accessed 8-28-2018.